

Description

The 4901 *Sn99 No Clean Solder Wire* is an electronic grade solder wire. It uses a high-purity, eutectic Sn99.3/Cu0.7 alloy, which is complemented with a no clean, synthetically refined, splatter-proof resin flux core. The 4901 solder meets J-STD-004B, ASTM B 32, and exceeds J-STD-006C specifications.

This solder is a great lead-free alternative to leaded solders. It is suitable, less costly replacement for SAC305.

The 4901 solders achieve a consistent solder and flux percentage through a state-of-the-art, extrusion, wire-drawing machine. This machine continually monitors the wire to prevent voids and ensure consistency, providing a top-grade solder wire.

Benefits & Features

- **Eutectic alloy** (liquidus = solidus temperature)
- **Alloy exceeds J-STD-006C and meets ASTM B 32 purity requirements**
- **Flux meets J-STD-004B**
- **The resin spreads like rosin-activated flux**
- **Virtually non-splattering**
- **Non-corrosive**
- **Non-conductive residue**
- **Halide free**
- **Suitable for Use in Food Facilities as a Non-Food Chemical**—Canadian and NFS recognition letters available on request

COMPLIANCE

- ✓ Dobb Frank ([DRC conflict free](#))
- ✓ REACH ([compliant](#))
- ✓ RoHS ([compliant](#))

Wire Sizes Availability

<i>Cat No.</i>	<i>Std. Wire Gauge</i>	<i>Diameter</i>		<i>Packaging</i>	<i>Sizes</i>
4901	21	0.81 mm	0.032 in	Spool	¼, ½, 1 lb, or 2 lb

General Flux Parameters

<i>Properties</i>	<i>Value</i>
Residue Removal	Not required
Flux Percentage	2.2%
Flux feature	Wets and spreads like a RA type flux and virtually non-splattering.
Shelf life	5 y

Continued on the next page

Flux Core Properties

The synthetically refined resin wets and spreads like a RA flux. This no clean flux is virtually non-spattering. It gives rise to a hard, non-conductive and non-corrosive residue.

Physical Properties	Method	Value
Flux Classification	J-STD-004B EN29454-1	RELO Type 1.1.3
Flux Type		Resin
Flux Activity		Low
Halides %(wt)		<0.05%
Solid Flux Color	Visual	Lightly opaque
Softening Point of Flux Extract		24 °C [75 °F]
Acid Number (mgKOH/g sample)	IPC-TM-650 2.3.13	190–210
Copper Mirror	IPC-TM-650 2.3.32	No removal
Silver Chromate—Chlorides + Bromides	IPC-TM-650 2.3.33	Pass
Solder Spread	IPC-TM-650 2.4.46	130 mm ²
Flux Residue Dryness	IPC-TM-650 2.4.47	Pass
Spitting of Flux-Cored Wire Solder	IPC-TM-650 2.4.48	0.30%
Corrosion Test	IPC-TM-650 2.6.15	Non-corrosive
Surface Insulation Resistance (SIR)	IPC-TM-650 2.6.3.3	$2.3 \times 10^{11} \Omega$
Bellcore (Telecordia)	Bellcore GR-78-CORE 13.1.3	$6.1 \times 10^{11} \Omega$
Electromigration	Bellcore GR-78-CORE 13.1.4	Pass
Post Reflow Residue	TGA Analysis	55%
Cleaning Requirements	—	Optional

Sn99.3/Cu0.7/Co Alloy Typical Literature Properties

Physical Properties	Value ^{a)}
Color	Silvery-white metal
Density @26 °C [78 °F]	7.4 g/cm ³
Tensile Strength	22 N/mm ² [3 100 lb/in ²]
Elongation	41%
Shear Strength	~23 N/mm ² [~3 300 lb/in ²]
Hardness, Brinell	9HB
Electrical Properties	Value
Volume Resistivity	12.3 μΩ·cm
Electrical Conductivity ^{b)}	13% IACS

a) N/mm² = mPa; lb/in² = psi;

b) International Annealed Copper Standard: 100% give 5.8×10^7 S/m.

Continued on the next page


Continued...

Thermal Properties	Value
Melting Point, Solidus	227 °C [442 °F]
Melting Point, Liquidus	227 °C [442 °F]
Tip Temperature Upper Limit	Do not exceed 400 °C [752 °F]
Coefficient of Thermal Expansion (CTE) ^{c)}	23.5 ppm/°C
Thermal Conductivity	~82 W/(m·K)
Specific Heat Capacity	~294 J/(kg·K)

NOTE: This table present typical literature values for Sn99.3/Cu0.7 alloys.

c) CTE for pure tin; unit conversions: ppm/°C = $\mu\text{m}/(\text{m}\cdot\text{K}) = \text{in}/\text{in}/\text{°C} \times 10^{-6} = \text{unit}/\text{unit}/\text{°C} \times 10^{-6}$

Solder Alloy Composition

Properties	Value	Properties	J-STD-006C
<i>MAIN INGREDIENTS</i>	<i>COMPOSITION</i>	<i>IMPURITIES</i> ^{a)}	<i>REQUIREMENTS</i>
Sn	99.3%	Sb	≤0.20% Max
Cu	0.7%	Ag	≤0.10% Max
		Bi	≤0.10% Max
		In	≤0.10% Max
		Pb	≤0.10% Max
		Au	≤0.05% Max
		As	≤0.03% Max
		Fe	≤0.02% Max
		Ni	≤0.01% Max
		Al	≤0.005% Max
		Zn	≤0.003% Max
		Cd	≤0.002% Max

a) Meets the requirements of J-STD-006C and meets ASTM B 32.

Storage

Protect from direct heat or sunlight. Store between 18 to 27 °C [65 to 80 °F].

Cleaning

The flux residue does not need to be removed for typical applications. If removal is desired, a solvent system like the *MG 4140* can be used. For best results, warm the cleaning solution to about 40 °C [104 °F].

Health and Safety


Please see the 4901 **Safety Data Sheet** (SDS) for more details on transportation, storage, handling and other security guidelines.

Health and Safety: Avoid breathing fumes. Wash hands thoroughly after use. Do not ingest.

HMIS® RATING

HEALTH:	* 1
FLAMMABILITY:	0
PHYSICAL HAZARD:	0
PERSONAL PROTECTION:	

NFPA® 704 CODES



Approximate HMIS and NFPA Risk Ratings Legend:

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

Packaging and Supporting Products

<i>Cat. No.</i>	<i>Form</i>	<i>Packaging</i>	<i>Net Weight</i>	
4901-112G	Solid wire	Pack of 25	113 g	0.25 lb
4901-227G	Solid wire	Pack of 3	227 g	0.5 lb
4901-454G	Solid wire	Spool	454 g	1.0 lb
4901-2LB	Bar	Bar	908 g	2.0 lb



Sn99 No Clean Solder Wire 4901 Technical Data Sheet

ISO 9001:2008 Registered Quality System. Burlington, Ontario, CANADA SAI Global File: 004008

4901

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)

+ (1) 905-331-1396 (International)

+ (44) 1663 362888 (UK & Europe)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: **Manufacturing & Support**
1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office
9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Warranty

M.G. Chemicals Ltd. warranties this product for 12 months from the date of purchase by the end user. *M.G. Chemicals Ltd.* makes no claims as to shelf life of this product for the warranty. The liability of *M.G. Chemicals Ltd.* whether based on its warranty, contracts, or otherwise shall in no case include incidental or consequential damage.

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный)

Факс: 8 (812) 320-02-42

Электронная почта: org@eplast1.ru

Адрес: 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.