

RW-2500-3 Revision 3 Page 1 of 5 August 2015

Specification RW-2500-3 TE 108-121006

THIN-WALL MARKER SLEEVES TW-TMS

Approved Signatories:

This document is electronically reviewed and approved by TE Connectivity.



RW-2500-3 Revision 3 Page 2 of 5 August 2015

1. REVISION HISTORY

Revision Number	Description of change	Date	Incorporated By
1	AFC 256	14/04/04	Alan Kean
2	AFC 372	14/04/04	Alan Kean
3	Refer to PCN	16/07/14 issued 08-2015	Lee Smith

2. SCOPE

This specification sheet, when used with RW-2500, defines the product characteristics and performance of TE Connectivity Thin-Wall Marker Sleeves.

The printing system developed for this marker sleeve is now obsolete. TE can only guarantee the physio-chemical nature of the product, and not any marking applied using non-recommended printing systems. Where non-standard systems are used, customers are required to carry out their own validation testing.

3. REQUIREMENTS

3.1. MATERIAL

The sleeving shall be fabricated from irradiated, thermally stabilized, modified polyvinylidene fluoride compound. It shall be homogeneous and essentially free from flaws, defects, pinholes, bubbles, seams, cracks or inclusions.

3.2. COLOR

The sleeves shall be supplied in white, unless otherwise specified.

3.3. PROPERTIES


The sleeves shall meet the requirements of Table 3.

3.4. FORM

The sleeves shall be cut lengths in accordance with Table 1.



RW-2500-3 Revision 3 Page 3 of 5 August 2015



Dimensions are in inches

Figure 1



RW-2500-3 Revision 3 Page 4 of 5 August 2015

TABLE 1 Sleeve Dimensions

	As Supplied			Recovered				
Product Description	Inside Diameter Minimum		Marking Length Minimum		Inside Diameter Maximum		Wall Thickness	
	in.	mm.	in.	mm.	in.	mm.	in.	mm.
TW-TMS-3/32-1.50	.093	2.36	1.60	39.41	.030	0.76	.017 <u>+</u> .003	0.43 <u>+</u> 0.08
TW-TMS-1/8-1.50	.125	3.17	1.60	39.41	.050	1.27	.017 <u>+</u> .003	0.43 <u>+</u> 0.08
TW-TMS-3/16-1.50	.187	4.74	1.57	38.65	.093	2.36	.018 <u>+</u> .003	0.46 <u>+</u> 0.08
TW-TMS-1/4-1.50	.250	6.35	1.55	38.14	.125	3.17	.018 <u>+</u> .003	0.46 <u>+</u> 0.08
TW-TMS-3/32-1.75	.093	2.36	1.90	47.00	.030	0.76	.017 <u>+</u> .003	0.43 <u>+</u> 0.08
TW-TMS-1/8-1.75	.125	3.17	1.90	47.00	.050	1.27	.017 <u>+</u> .003	0.43 <u>+</u> 0.08
TW-TMS-3/16-1.75	.187	4.74	1.85	45.70	.093	2.36	.018 <u>+</u> .003	0.46 <u>+</u> 0.08
TW-TMS-3/16-OX-1.75	.187	4.74	1.85	45.70	.062	1.57	.022 <u>+</u> .003	0.55 <u>+</u> 0.08
TW-TMS-1/4-1.75	.250	6.35	1.81	44.70	.125	3.17	.018 <u>+</u> .003	0.46 <u>+</u> 0.08
TW-TMS-1/4-OX-1.75	.250	6.35	1.81	44.70	.093	2.36	.022 <u>+</u> .003	0.56 <u>+</u> 0.08

TABLE 2

Mandrel Dimensions for Heat Shock, Heat Aging and Low Temperature Flexibility

Tubing Size	Mandrel Diameter		
Tubing Size	in	mm	
3/32 through 3/16	5/16	7.9	
1/4 through 3/4	3/4	19.0	



RW-2500-3 Revision 3 Page 5 of 5 August 2015

TABLE 3 Requirements

PROPERTY	UNIT	REQUIREMENT	RW-2500 TEST METHOD	
PHYSICAL				
Dimensions	Inches	In accordance with Table 1		
Dimensional Recovery	Inches	In accordance with Table 1	RW-2500 Section	
3 minutes at 200°C (392°F)	mones	in accordance with rable 1	4.3.1.1	
Longitudinal Change 3 minutes at 200°C (392°F)	Percent	10 maximum	ASTM D 2671	
Tensile Strength	MPa (psi)	10.3 (1500) minimum	RW-2500 Section 4.3.2.1 ASTM D 2671	
Ultimate Elongation	Percent	200 minimum	2 inches/minute	
Specific Gravity		1.38 maximum	RW-2500 Section 4.3.3 ASTM D 2671	
Low Temperature Flexibility 4 hours at -55°C (-67°F)		No cracking	RW-2500 Section 4.3.5.1	
Heat Shock 4 hours at 250°C (482°F)		No dripping, flowing, or cracking	RW-2500 Section 4.3.6.1	
Heat Aging 168 hours at 175°C (347°F)		No cracking	RW-2500 Section 4.3.7.1	
Copper Contact Corrosion 16 hours at 150°C (302°F)		No pitting or blackening of copper	RW-2500 Section 4.3.14.1	
Pull-Off Force				
Size: 3/32	N (Pounds)	26 (6.0) maximum	DIM OFOO Occiden	
Size: 1/8	N (Pounds)	31 (7.0) maximum	RW-2500 Section 4.3.8	
Size: 3/16	N (Pounds)	35 (8.0) maximum		
Size: 1/4	N (Pounds)	40 (9.0) maximum		
ELECTRICAL Dielectric Strength	kV/mm (V/mil)	19.7 (500) minimum	RW-2500 Section 4.3.11.1 ASTM D 2671	
Volume Resistivity	ohm-cm	10 ¹⁴ minimum	RW-2500 Section 4.3.12.1 ASTM D 2671	
CHEMICAL Corrosive Effect 16 hours at 150°C (302°F)		Non Corrosive	RW-2500 Section 4.3.13.1 ASTM D 2671	
Flammability (FED-STD-228)		Burn time shall not exceed one minute, and not more than 25% of indicator flag shall be burned or charred. No dripping or flowing.	RW-2500 Section 4.3.15.3	
Fungus Resistance		Rating of 1 or less	ASTM G 21	
Water Absorption 24 hours at 23°C (73°F)	%	0.5 maximum	ASTM D 570	



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов:
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001:
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный)

Факс: 8 (812) 320-02-42

Электронная почта: org@eplast1.ru

Адрес: 198099, г. Санкт-Петербург, ул. Калинина,

дом 2, корпус 4, литера А.