



Silicone Rubber Cold Shrink Connector Insulators 8440 Series

Data Sheet

1.0 Product Description

3M™ Cold Shrink Connector Insulators 8440 Series are open ended, silicone rubber, tubular sleeves. The sleeves are factory expanded and assembled on a removable supporting plastic core. Each rubber assembly is supplied for field installation in this pre-stretched condition. As the core is unwound, the insulating sleeve shrinks to form a tight seal. Three sizes of Cold Shrink Insulators cover terminal lug barrels and three sizes of Cold Shrink Insulators cover inline connectors. Each insulator type, collectively has an application range of 0.35" (8,86 mm) to 0.95" (24,13 mm) for installations on #6 AWG to 3/0 AWG.

- Simple installation, requires only workman's hands.
- No tools required.
- No heat required for installation.
- Seals tight, retains its resiliency and pressure even after years of aging and exposure.
- Resists moisture.
- Wide range, size accommodation.
- Resists acids and alkalies.
- Resists ozone and ultraviolet light.
- Resists fluid splashes.
- Resists fire - will not support flame.
- Operating temperature range - 66° F/ - 55° C to 500° F/260° C.


2.0 Applications

- Primary electrical insulation for all solid dielectric (rubber and plastic) insulated wire and cable splices rated to 1000 volts.
- Electrical Aircraft cables.
- For indoor, outdoor, in cable tray for overhead use.
- Physical protection and moisture sealing for high voltage, air insulated connectors and lugs.
- Insulation of secondary splices, copper and aluminum conductors.
- Sheath repairs.
- Insulation for inline conductor transition connector.

3.0 Data: Physical & Electrical Properties

High Stretch Silicone Rubber Typical Physical Properties

<u>Test Method</u>	<u>Typical Values</u>
Color	Grey
100% Modulus ASTM D412-75	180 psi (1.24MPa)
Ultimate Tensile ASTM D412-75	1240 psi (8.55 MPa)
Die B Tear ASTM D624B-73	185 psi (1.28 MPa)
Shore A Hardness ASTM D2240-75	48
Specific Gravity	1.23
Permanent Set 100% Strain - 22 hours @ 212° F/100° C	7.1%
Dielectric Strength ASTM D149-75 @1.78 mm thickness	554 Volts/mil (21.8 MV/m)
Dielectric Strength 168 hours in H2O @194° F/90° C	543 Volts/mil (21.4 MV/m)



Part Number	Cable Range AWG	Application Range Inches (mm)		Dimensions Inches (mm)	
		Min. Dia.* for Seal	Max. Dia.** Insulator Covers	A Length	B I.D. (Core)
8443-2	6 - 2	.350 (8.86)	.560 (14.22)	1.4 (36)	0.68 (17.3)
8443-6.5	6 - 2	.350 (8.86)	.560 (14.22)	5.2 (132)	0.68 (17.3)
8445-2.5	2 - 1/0	.420 (10.7)	.720 (18.29)	1.7 (43)	0.84 (21.3)
8445-7.5	2 - 1/0	.420 (10.7)	.720 (18.29)	6.2 (158)	0.84 (21.3)
8447-3.2	1/0 - 3/0	.550 (14)	.950 (24.13)	2.3 (57)	1.07 (27.2)
8447-8	1/0 - 3/0	.550 (14)	.950 (24.13)	6.8 (172)	1.07 (27.2)

Table 1

4.0 Specifications Product

Exposed metallic connectors joining power cable conductors rated 1000 volts or less shall be covered with 3M™ 8440 Series Silicone Cold Shrink tubular rubber insulation.

The inline connections shall be insulated in accordance with the instructions provided with the 3M™ Cold Shrink Connector Insulator 8443-6, 8445-7.5, and 8447-8. The connecting barrel portion of terminal lugs shall be insulated in accordance with the instructions provided with the 3M™ Cold Shrink Connector Insulators 8443-2, 8445-2.5, and 8447-3.2.

Engineering/Architectural

A silicone Cold Shrink Connector Insulators must be capable of normal operation through a temperature range of -66°F/ -55°C to 500°F/260°C. It must be usable without additional covering or adhesive both indoors and outdoors, in cable tray or overhead applications on cables rated up to 1000V. It must be applied without additional heat or flame and, when applied according to manufacturer's directions, be immediately energizable. It must not support flame or be adversely affected by moisture, mild acids or alkalis, ozone or ultraviolet light. It must provide resistance to aircraft fluids and be compatible with all rubber and plastic insulated power cables.

5.0 Performance Tests

A. Flammability Test

The test for flammability of the 3M Cold Shrink Insulators 8440 Series was conducted with specimens positioned both vertically and horizontally per specification BSS 7230. The silicone rubber insulation passed the Flammability Test of BSS 7230 without supporting a flame. In addition, these insulators were also subjected to a gas flame test as outlined in paragraph 4.4.15 of MIL-C-24643A and met the passing criteria as specified. No fuse was blown during the one hour flame exposure.

B. Humid Environment

Tests to verify electrical integrity through conditions of high humidity were run per Mil Standard 202-Method B. The test duration was for 10 days at 104°F/40°C and 95% RH. Typical test values are found in Table 2.

C. Ultraviolet Resistance

After 1000 hours of testing in a Weather-O-Meter according to Specifications ASTM D750 and ASTM G23, the silicone rubber insulation exhibited no crazing, cracking or change in surface appearance.

Test	Insulation Resistance	Withstand	Result
Before	3.0 x 10 ¹²	2500 V-rms	Pass
After	2.5 x 10 ¹²	2500 V-rms	Pass

Table 2

D. Thermal Shock

Assembled units from the fluid resistance test were used for the thermal shock evaluation. The units were subjected to 15 cycles of the following thermal shock sequence:

1. 30 minutes at -66°F/ -55°C.
2. 5 minutes at 74°F/23°C.
3. 30 minutes at 500°F/260°C.
4. 5 minutes at 74°F/23°C.

The insulation resistance values and results of test are found in Table 3.

Fluid	Test	Insulation Resistance	Withstand	Result
Monsanto L.D.	Before	1.5×10^{13} ohms	2500 V-rms	Pass
	After	1.0×10^{12} ohms	2500 V-rms	Pass
Jet A	Before	7.0×10^{12} ohms	2500 V-rms	Pass
	After	1.7×10^{12} ohms	2500 V-rms	Pass
MIL-L-7808	Before	3.5×10^{12} ohms	2500 V-rms	Pass
	After	6.5×10^{12} ohms	2500 V-rms	Pass
MIL-L-23699	Before	8.0×10^{12} ohms	2500 V-rms	Pass
	After	3.5×10^{12} ohms	2500 V-rms	Pass
5% Saline	Before	9.0×10^{12} ohms	2500 V-rms	Pass
	After	6.5×10^{12} ohms	2500 V-rms	Pass

Table 3

E. Altitude

Electrical integrity at high altitudes was determined by testing to Mil Standard 1344A, Test method 1004.1. Typical test values are found in Table 4.

Altitude	Insulation Resistance	Withstand	Result
50,000	1.0×10^{11} ohms	2500 V-rms	Pass
70,000	1.8×10^{12} ohms	2500 V-rms	Pass

Table 4

F. Heat Aging

Installed silicone rubber insulators were subjected to an eight hour heat aging test at 500°F/260°C. Other units were subjected to 401°F/205°C for 30 days. The silicone rubber remained resilient and showed no sign of deterioration.

G. Fluid Resistance

To determine the affect of a fluid splash on insulated connected assemblies, the units were subjected to ten cycles of the following test sequence.

1. One minute fluid soak.
2. 24 hour, 74°F/23°C ambient dry.
3. Insulation resistance measurement.
4. 2.4 kV-rms withstand.

Results from the fluid resistance test are found in table 5.

6.0 Maintenance

Components of 3M™ Silicone PST Cold Shrink Connector Insulators are stable under normal storage conditions for a period of three years from the date of manufacture. The Cold Shrink Insulators are not impaired by freezing or overheating due to the ambient temperatures found in storage or shipping. Normal storage and stock rotation are recommended.

7.0 Availability

3M™ Silicone PST Cold Shrink Connector Insulators 8440 Series are available through your local authorized 3M electrical distributor.

Fluid Splash Test Insulation Resistance/2500 V-rms Withstand

Fluid	Monsanto L.D.	Jet A	MIL-L-7808	MIL-L-23699	5% Saline
Initial	1.5 x 10 ¹³ /Pass	7.2 x 10 ¹² /Pass	3.5 x 10 ¹² /Pass	8.0 x 10 ¹² /Pass	9.0 x 10 ¹² /Pass
1	3.0 x 10 ⁹ ohms	2.0 x 10 ¹² ohms	8.0 x 10 ¹² ohms	2.5 x 10 ¹² ohms	3.5 x 10 ¹² ohms
2	1.2 x 10 ⁹ ohms	1.2 x 10 ¹² ohms	2.0 x 10 ¹² ohms	5.0 x 10 ¹² ohms	5.0 x 10 ¹² ohms
3	4.0 x 10 ⁷ ohms	1.2 x 10 ¹² ohms	2.5 x 10 ¹² ohms	4.0 x 10 ¹² ohms	3.5 x 10 ¹² ohms
4	1.8 x 10 ⁷ ohms	8.0 x 10 ¹¹ ohms	3.0 x 10 ¹² ohms	3.0 x 10 ¹² ohms	4.0 x 10 ¹² ohms
5	8.0 x 10 ⁶ ohms	3.0 x 10 ¹¹ ohms	2.0 x 10 ¹² ohms	2.5 x 10 ¹² ohms	6.0 x 10 ¹² ohms
6	6.0 x 10 ⁶ ohms	2.0 x 10 ¹¹ ohms	1.8 x 10 ¹² ohms	2.0 x 10 ¹² ohms	7.0 x 10 ¹² ohms
7	5.0 x 10 ⁶ ohms	1.8 x 10 ¹¹ ohms	1.0 x 10 ¹² ohms	2.5 x 10 ¹² ohms	9.0 x 10 ¹² ohms
8	4.0 x 10 ⁶ ohms	1.0 x 10 ¹¹ ohms	1.0 x 10 ¹¹ ohms	1.4 x 10 ¹² ohms	3.0 x 10 ¹² ohms
9	4.0 x 10 ⁶ ohms	1.0 x 10 ¹¹ ohms	6.5 x 10 ¹¹ ohms	1.0 x 10 ¹² ohms	3.0 x 10 ¹² ohms
10	3.5 x 10 ⁶ ohms	7.0 x 10 ¹⁰ ohms	5.0 x 10 ¹¹ ohms	1.2 x 10 ¹² ohms	5.0 x 10 ¹² ohms

Table 5

Approximate Installed Weight			
Terminal Lug Insulators		Inline Connector Insulators	
Part No.	Weight oz. (gm)	Part No.	Weight oz. (gm)
8443-2	0.123 (3.5)	8443-6.5	0.388 (11.0)
8445-2.5	0.190 (.54)	8445-7.5	0.564 (16.0)
8447-3.2	0.335 (9.5)	8447-8	0.776 (22.0)

Table 6

IMPORTANT NOTICE

Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use.

Warranty; Limited Remedy; Limited Liability. This product will be free from defects in material and manufacture as of the date of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any loss or damage arising from this 3M product, whether direct, indirect, special, incidental or consequential regardless of the legal theory asserted.**



Electrical Products Division

6801 River Place Blvd.
Austin, TX 78726-9000
800/245-3573
www.3M.com/elpd



Printed on 50% recycled paper
with 10% post-consumer

Litho in USA
©3M 2003 78-8124-5813-7 Rev. B



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный)

Факс: 8 (812) 320-02-42

Электронная почта: org@eplast1.ru

Адрес: 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.