

3M

Scotchlite™

High Gain Reflective Sheeting

7610

Technical Data

May, 2003

Product Description 3M™ Scotchlite™ Sheeting 7610 is a high gain reflective industrial grade sheeting, exposed-lens, retroreflective, plastic-based material, pre-coated with a pressure-sensitive adhesive that is covered with a removable protective liner that offers very high retroreflective efficiency and small optical elements.

Construction	Color	Lens	Liner
	Light gray	Exposed	Yes

Typical Physical Properties **Note: The following technical information and data should be considered representative or typical only, and should not be used for specification purposes.**

Thickness	Applied: .004 in. (.010 cm) Liner: .006 in. (.015 cm)
Typical Luminance Factor	-4° reading: 900X Skewed 45° reading: 700X
Temperature Resistance	Continuous exposure: 175°F (79°C) Intermittent exposure (30 min.): 250°F (121°C)

- Features**
- Sealed-lens surface.
 - Thin construction.
 - Exceptional reflective gain.
 - Ease of angularity.
 - Ease of conformability.
 - For various shaped items, including cylinders.
 - Angularity allows pickup from moving objects.

Available Sizes	Widths: 1/2 in. (1.27 cm), 3/4 in. (1.90 cm), 1 in. (2.54 cm), 2 in. (5.08 cm), Lengths: 50 yds. (45.7 m)
-----------------	--

Custom widths and lengths available on request, subject to minimum order requirements.

- Application Ideas**
- This industrial grade reflective sheeting is recommended for applications demanding very high retroreflective efficiency; however, its use is limited to manual application, since the material is too thin to perform in automatic application equipment.

3M™ Scotchlite™ High Gain Reflective Sheeting 7610

Application Techniques	Hand application is recommended, as the material is too thin to perform in application equipment. Application may be made at temperatures as low as 10°F (-12°C) to a clean and dry surface; however, it is recommended that application be made at 60°F (16°C) to 80°F (27°C). Avoid touching the reflective surface, since skin oils will reduce the retroreflective brightness. Brightness can be restored by cleaning with a soft cloth and a dilute solution of mild detergent in water. The sheeting will remain serviceable for many years when properly applied to a suitable substrate and used in typical indoor or outdoor environments. Use in a high temperature environment (above 350°F [177°C]) for an extended period of time could permanently reduce retroreflective efficiency.
Storage Conditions	3M™ Scotchlite™ High Gain Reflective Sheeting 7610 should be stored in a cool, dry area, preferably at 70-75°F (20-24°C) and 30-50% relative humidity, and horizontally in the shipping carton. Avoid pressure from stacking.
Shelf Life	Product should be applied within one year after purchase.
For Additional Information	To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/packaging. Address correspondence to: 3M Industrial Adhesives and Tapes Division, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55144-1000. Our fax number is 651-778-4244. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.
Important Notice	3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's application.
Limitation of Remedies and Liability	If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.

ISO 9002

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9002 standards.



**Industrial Business
Industrial Adhesives and Tapes Division**
3M Center, Building 21-1W-10, 900 Bush Avenue
St. Paul, MN 55144-1000



Recycled Paper
40% pre-consumer
10% post-consumer

Printed in U.S.A.
©3M 2003 70-0710-0278-9 (5/03)



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный)

Факс: 8 (812) 320-02-42

Электронная почта: org@eplast1.ru

Адрес: 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.