
Product Description

3MTM BumponTM Protective Products Molded Shapes - Colored and Clear Series are pressure-sensitive. adhesive-backed polyurethane products. They can be used as feet, stops, spacers, and protectors in many applications.

The urethane is a durable, resilient elastomer. The aggressive, high tack, pressure sensitive adhesive is protected with a release liner making application fast and easy.



Features

All 3M™ Bumpon™ Protective Products feature a plasticizer-free, urethane composition which exhibits:

- Excellent skid resistance
- Long aging resiliency will not crack or harden
- Abrasion resistance
- Resistance to marring and staining

Application Ideas

Use almost anywhere slamming, scratching, nicking, scuffing, marring, sliding, vibration, or noise could be a problem for your product.

- **Feet** on the bottom of small appliances, desk top or handheld electronic devices, electronic cabinetry, telephones, keyboards, foot pedals, scales, clocks, speakers, dispensers, and computers.
- Stops for cabinet doors, lids, and drawers.
- Spacers for picture frames to provide alignment; for electronic and automotive applications as an aid in assembly.
- Protectors to prevent damage in shipping, and keep parts from direct contact with each other.




3M[™] Bumpon[™] Protective Products

Molded Shapes - Colored and Clear Series

SJ5000 • SJ5300 • SJ5400 • SJ5500 • SJ5700 • SJ6100

3M[™] Bumpon[™] Protective Products

Molded Shape Number



Product Number

Colors


Width inches (mm) Height inches (mm) Pad Format

Bumpon \$J5012, \$J5312*, \$J5412**

Black, Brown, White, Gray, Transparent*,

True White** 0.50 (12.7) 0.14 (3.5) 7x8 (56)


Cylindrical Shapes (with flat tops)



Bumpon SJ5744, SJ5344*

Black, Transparent*

0.75 (19.1) 0.16 (4.1) 4x10 (40)




Bumpon SJ5076, SJ5376*

Black, Transparent*

0.315 (8.0) 0.110 (2.8) 8x7 (56)

Cylindrical Shapes (with concave tops)

Molded Shape Number




Product Number

Colors Width inches (mm) Height inches (mm) Pad Format


Bumpon SJ5001

Black 0.50 (12.7) 0.14 (3.5) 5x8 (40)



Bumpon SJ5009, SJ5309*


White, Gray, Brown, Black Transparent* 0.88 (22.3) 0.40 (10.1) 3x8 (24)



Bumpon SJ5532

Gray, Black 1.88 (47.7) 0.66 (16.7) Separate Parts

Molded Shape Number



Product Number


Colors Width inches (mm) Height inches (mm) Pad Format

Bumpon SJ5302*, SJ5402**

Transparent*, True White** 0.312 (7.9) 0.085 (2.2)

8x18 (144)

Hemispherical Shapes



Bumpon SJ5003*

Black, Brown, Gray, Transparent* 0.44 (11.1) 0.20 (5.0) 8x7 (56)



Bumpon SJ5306*, SJ5406**

Transparent*, True White** 0.375 (9.5) 0.150 (3.8) 6x8 (48)

Molded Shape Number


Product Number

Width inches (mm)

Height inches (mm)


Colors

Pad Format




Bumpon SJ5017, SJ5317*

White, Gray, Black, Transparent* 0.75 (19.0) 0.38 (9.6) 4x10 (40)



Bumpon SJ5027, SJ5327*

White, Gray, Brown, Black, Transparent* 0.63 (16.0) 0.31 (7.9) 5x8 (40)



Bumpon SJ5382*

Transparent* 0.25 (6.4) 0.075 (1.9) 8x18 (144)


*Bumpon SJ5300 series identifies transparent products. **Bumpon SJ5400 series identifies true white products.

Note: All dimensions ± 0.02 inches or ± 0.5 mm measured without the adhesive liner.

Important: Some Bumpon molded shapes listed (or specific color versions) may require special minimum order quantities. Consult your local 3M representative or our website: www.3M.com/Bumpons.

3M™ Bumpon™ Protective Products

Molded Shape Number



Product Number Bumpon SJ5705, SJ6105


 Colors
 Black

 Width inches (mm)
 1.275 (32.4)

 Height inches (mm)
 0.250 (6.4)

 Pad Format
 3x3 (9)

Molded Shape Number



Product Number Bumpon SJ5514


 Colors
 White, Gray, Black

 Width inches (mm)
 0.81 (20.6)

 Height inches (mm)
 0.52 (13.1)


 Pad Format
 4x1 (4)

Tapered Square Shapes




Bumpon SJ5007, SJ5307*

Black, White, Transparent* 0.413 (10.4) 0.98 (2.5) 6x9 (54)




Bumpon SJ5018, SJ5318*

White, Gray, Brown, Black, Transparent* 0.50 (12.7) 0.23 (5.8) 8x10 (80)



Bumpon SJ5008, SJ5308*

White, Gray, Black, Transparent* 0.50 (12.7) 0.12 (3.1) 8x10 (80)




Bumpon SJ5023, SJ5323*

White, Gray, Brown, Black, Transparent* 0.81 (20.5) 0.30 (7.6) 4x9 (36)

Note: All dimensions ± 0.02 inches or ± 0.5 mm measured without the adhesive liner.

Top Hat and Continuous Strip Shapes

Molded Shape Number



Product Number Bumpon SJ6115 - Top Hat


 Colors
 Black

 Diameter of Brim, inches (mm)
 0.625 (15.9)

 Height of Brim, inches (mm)
 0.093 (2.36)


 Total Height, inches (mm)
 0.187 (4.75)

 Form
 5x8 (40)



Bumpon SJ6125 - Top Hat

Black 0.625 (15.9) 0.093 (2.36) 0.250 (6.35) 5x8 (40)



Bumpon SJ5510 - Continuous Strip*

White, Gray, Black, Brown Width, inches (mm): 0.50 (12.7) Height, inches (mm): 0.15 (3.88)

50' rolls, 5 rolls per case

Note: Dimensions for Bumpon SJ6115 and Bumpon SJ6125 ±0.005 inches (±0.13 mm) for diameter ±0.015 inches (±0.38 mm) for height measured without adhesive liner. Bumpon Top Hat products were created as an optional, non-skid foot shape, to be used in a recess (see page 7). They provide high resistance to removal, knock-off or shearing, when used in conjunction with a recessed location.

*Continuous molded strip can be cut by the customer to a specific length. The surface has lines that appear every 9" on the strip.

Important: Some Bumpon molded shapes listed (or specific color versions) may require special minimum order quantities. Consult your local 3M representative or our website: www.3M.com/Bumpons.

Special Products

Custom Shape and Color

3M can match most colors and customize shapes to your specifications. 3M has over 100 available standard and custom molded shapes. Electronic format (CAD and PDF) drawings are available on request.

Special Easy Strip Packaging

Packaged into strips or die cut and perforated pads can help simplify some assembly operations. Product currently available:

- 3M™ Bumpon™ Protective Product SJ5518 die cut perforated on pads of 64
- 3MTM BumponTM Protective Product SJ5508 die cut and perforated on pads of 64
- 3MTM BumponTM Protective Product SJ5523 4x1 matrix separated by perforations
- 3M™ Bumpon™ Protective Product SJ5514 4x1 matrix separated by perforations

Note: Custom Bumpon products may require a qualifying minimum quantity and/or a one time set-up charge. Call your local 3M sales representative for more information.

^{*}Bumpon SJ5300 series identifies transparent products.

Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

	3M™ Bumpon™ Protective Products			
	3M Test Method	SJ5000 SJ5500 SJ5700	SJ5300 SJ5400	SJ6100
Hardness, Shore M	ASTM-D2240	72	75	72
Resilience, %	ASTM-D2632, 0.125" sample	30	5	30
Kinetic Coefficient of Friction (Mk) (Dependent on Test Surface) ¹	ASTM-D1894 Stainless Steel Glass Formica® laminate Wood	>1 >1 0.9-1.4 0.9-1.4	>1 >1 0.9-1.4 0.9-1.4	>1 >1 0.9-1.4 0.9-1.4
Abrasion Resistance (Taber H18, 1kg) g/1000 cycles²	ASTM-C501	1.7-1.9	0.13	1.7-1.9
Tensile, Ibs/in² (MPa)²	ASTM-D412, Die A	600 (4.1)	740 (5.1)	600 (4.1)
Elongation,% ²	ASTM-D412, Die A	100	65	100
Dielectric Strength, volts/mil ²	ASTM-D1000	200	370	200
Stain Resistance ³	3M-24 hours @ 158°F against white paint 7 days exposed to UV.	No Staining	No Staining	No Staining
Flammability Listing	UL-94HB	Pass; UL Recognized	Not UL Recognized	Pass; UL Recognized
Application Temperature		40°F (5°C) to 125°F (52°C)		
Service Temperature	Constant: Intermittent:	-30°F (-34°C) to 150°F (66°C) Up to 225°F (107°C)		
Solvent and Fuel Resistance ³	24 hour immersion 5% Detergent in wate 25% Ammonia in wat Bleach Hydrochloric Acid (1 Normal Solution) Diesel Fuel Auto Oil Isopropyl Alcohol Heptane Toluol Lacquer Thinner	• •		

Notes:

¹Two important laws of friction applicable to Bumpon products are: (1) Friction is independent of the area of contact between solids and (2) friction is proportional to the load between solid surfaces. Thus, if the load (weight) is doubled the force required to cause sliding is also double. This is expressed mathematically as follows: Sliding Force = M_k x weight.

²These properties were run on sheet material from the same materials as the individual Bumpon products

³Reference test for 24 hours. Results may vary for different product application conditions.

Relative Adhesive Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

	3M™ Bumpon™ Protective Products				
	SJ5000 SJ5500 SJ5700	SJ5300 SJ5400	SJ6100		
Adhesive:	Natural Rubber R-30	Acrylic A-20	Synthetic Rubber R-25		
Initial Adhesion Low Surface Energy: High Surface Energy:	Good Good	Poor Fair	Excellent Excellent		
Adhesion (Peel) Low Surface Energy: High Surface Energy:	Good Good	Poor Good	Excellent Excellent		
Static Shear 75°F (25°C): 120°F (49°C): 158°F (70°C)	Excellent Good Poor	Excellent Excellent Excellent	Excellent Good Fair		
Dynamic Shear:	Good	Excellent	Good		
Solvent Resistance:	Good	Excellent	Good		

Adhesive Performance

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

The following table on peel adhesion provide representative performance characteristics of the adhesive systems used in the construction of $3M^{TM}$ Bumpon Protective Products molded series products.

90° Peel Adhesion

*Peel Force, oz. Per 1/2 inch

	3M™ Bumpon™ Protective Products					
	SJ5000 SJ5500 SJ5700	SJ5300 SJ5400	SJ6100			
Substrate:	Natural Rubber R-30	Acrylic A-20	Synthetic Rubber R-25			
Polypropylene	25	3	52			
Polystyrene	25	11	55			
ABS	25	25	55			
Stainless Steel	22	25	55			
Aluminum	22	25	55			

^{*3}M Test Method TM-2011; 72 hour dwell, 1/2 inch wide samples pulled at 12 inches per minute. Testing completed using Bumpon Resilient Rollstock products SJ5816, SJ6016, and SJ6216, which use the same adhesive system as the molded series products.

Application Techniques


To obtain maximum adhesion, surfaces must be unified, dry, and free of contaminants. Surface contact is essential to adhesive performance. To maximize contact on a substrate:

- Clean surfaces with low strength solvent such as isopropyl alcohol (rubbing alcohol) or heptane.*
- Apply firm pressure to help increase the cold flow and contact of the adhesive with the substrate.
- Allow time (dwell) to increase the surface contact and adhesion (see illustrations below).

*Note: Be sure to follow the manufacturer's precautions and directions for use when using solvents.

Adhesive Adhesive Adhesive Bonding Surface After Rubdown (More Contact) Adhesive Bonding Surface After Dwell Time (Excellent Contact) Adhesive Bonding Surface

Adhesive



Environmental Exposure

Colored and transparent 3MTM BumponTM Protective Products are intended for interior applications where resilience and other physical properties will remain unchanged. When exposed to UV light for extended periods some slight discoloration or yellowing may occur.

Bumpon products may be used outdoors in a protected area with some discoloration possible; colored Bumpon products may chalk.

Simultaneous exposure to high humidity and temperature may degrade (soften) the Bumpon product urethane.

Product Selections Considerations

Alignment


Alignment is more difficult with a rectangular shaped 3MTM BumponTM Protective Product when no recess is provided.

Circular shaped product



(top view)


Rectangular shaped product



(top view)

Point of Contact


The point of contact provides either a large contact area or a very small (point) contact area depending on the shape of the Bumpon product.



Increased load capacity

· Better wear resistance

Hemisphere




- · Increased sound dampening
- · Increased energy absorption

Profile

The profile is defined by the height and the diameter (or width) of the Bumpon product.




- · Increased load capacity
- Less susceptible to being sheared off substrate



- · Better hear dissipation
- Not recommended if sideways shearing is possible

Recess

A recess is not necessary; however, there are several benefits to providing a recess.



- · Provides target area for the Bumpon product during attachment process
- · Improves adhesion performance: impact absorption and shear strength
- · Provides neater appearance
- · Provides uniform location

Storage

Store in original cartons at 60° to 80°F (16° to 27°C) and 40 to 50% relative humidity.

Shelf Life

To obtain best performance, use this product within 18 months from date of manufacture.

Regulatory

For regulatory information about this product, refer to our website at 3M.com.

For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-251-8634. Address correspondence to: 3M, Electronics Markets Materials Division, 3M Center, Building 225-3S-06, St. Paul, MN 55144-1000. Our fax number is 651-778-4244 or 1-877-369-2923. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability.

This product will be free from defects in material and manufacture at the time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.











Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов:
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001:
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный)

Факс: 8 (812) 320-02-42

Электронная почта: org@eplast1.ru

Адрес: 198099, г. Санкт-Петербург, ул. Калинина,

дом 2, корпус 4, литера А.