



331 Flux-Cored Wire

Organic Cored Wire for Lead-free and Leaded Alloys

Product Description

Kester 331 organic flux is a water-soluble formula for use in flux-cored solder wire. This cored solder version of the popular 2331-ZX Neutral Organic Water Soluble Liquid Flux is more effective than rosin fluxes in soldering difficult metals. The same fast action and mild properties are exhibited with 331 Organic Flux as with the liquid 2331-ZX. The flux is more heat stable than most organic fluxes, resulting in minimal smoke and odor. The residue can be completely removed with a simple heated water rinse. Deionized water is suggested to prevent introduction of chemistries from unknown water sources.

Performance Characteristics:

- Excellent solderability to a wide variety of metalizations
- Easy removal in hot DI water
- Compatible with leaded and lead-free alloys
- Classified as ORH1 per J-STD-004



RoHS Compliance

Kester does not determine any applicable Restriction of Hazardous Substances (RoHS) exemptions for our lead containing products at the user level. (Applies only if this core flux is combined with a lead-free alloy)

Reliability Properties

Copper Mirror Corrosion: High
Tested to J-STD-004, IPC-TM-650, Method 2.3.32

Silver Chromate: Fail
Tested to J-STD-004, IPC-TM-650, Method 2.3.33

Fluorides by Spot Test: Pass
Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1

Corrosion Test: High
Tested to J-STD-004, IPC-TM-650, Method 2.6.15

Chloride and Bromides: 1.2%
Tested to J-STD-004, IPC-TM-650, Method 2.3.35

Surface Insulation Resistance (SIR), (typical): Pass
Tested to J-STD-004, IPC-TM-650, Method 2.6.3.3

	Blank	331
Day 1	1.9*10 ¹⁰ Ω	2.0*10 ⁹ Ω
Day 4	2.2*10 ¹⁰ Ω	7.8*10 ⁹ Ω
Day 7	1.7*10 ¹⁰ Ω	4.1*10 ⁹ Ω

Availability

331 is available in a wide variety of alloys, wire diameters and flux percentages. The most common alloys are Sn63Pb37, Sn96.5Ag3.0Cu0.5 and K100LD. Please refer to www.kester.com for wire diameters, flux percentages and roll sizes that are available.

Note: Core size 50, 58 and 66 = 1.1%, 2.2% and 3.3% flux core.

Process Considerations

Solder iron tip temperatures are most commonly between 315-343°C (600-650°F) for Sn63Pb37 and Sn62Pb36Ag02 alloys, and 371-400°C (700-750°F) for lead-free alloys. Heat both the land area and component lead to be soldered with the iron prior to touching the land with the cored wire. Do not apply the wire directly to the soldering iron tip. If needed, Kester 2331-ZX organic flux may be used as a compatible liquid flux to aid in reworking soldered joints. Kester 2331-ZX is available in Flux-Pens.

Cleaning

The 331 flux residue is conductive and will cause corrosion of metal parts over time. Residue removal should be completed within 48 hours. 331 Organic Flux has the advantage over many competitive water-soluble flux formulations in that the residue is easily and completely removed with plain hot water (120°F-140°F degrees). Softened tap water or deionized water is recommended for high reliability. Use of hard or high mineral content tap water will increase ionic cleanliness measurements.

Storage and Warranty Period

Storage must be in a dry, non-corrosive environment between 10-40°C (50-104°F). The surface may lose its shine and appear a dull shade of grey. This is a surface phenomenon and is not detrimental to product functionality. Flux-cored solder wire has a limited warranty period determined by the alloy used in the wire. For alloys containing more than 70% lead, the warranty period is 2 years from the date of manufacture. Other alloys have a warranty period of 3 years from the date of manufacture.

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet (SDS) and warning label before using this product.



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный)

Факс: 8 (812) 320-02-42

Электронная почта: org@eplast1.ru

Адрес: 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.