

Description

The 8334 *Super Glue, Gel* is a quick curing, solvent-less, high viscosity cyanoacrylate adhesive.

Applications & Usages

Its primary application is to bond parts together without the need for heat or pressure. This adhesive is well suited to bond rubber to rubber, plastic to plastic, rubber to metal, and plastic to metal applications.

This adhesive is not intended as a structural adhesive to join load bearing structures.

Benefits and Features

- **Bonds a wide variety of substrates**
- **Typical handling time of only 25 seconds**
- **Strong chemical resistance**

ENVIRONMENT

- ✓ RoHS
- ✓ REACH compliant

Usage Parameters

| <i>Properties</i> | <i>Value</i> |
|--|--------------|
| Typical Handling Time ^{a)} | 25 s |
| Service Cure ^{a, b)} @22 °C [72 °F] | >24 h |
| Cure Type | Humidity |
| Shelf Life | 3 y |

a) Assumes 50% relative humidity.

b) As well as humidity, the type of material being bonded, bond gap, and temperature, may change the cure time.

Temperature Ranges

| <i>Properties</i> | <i>Value</i> |
|--------------------------------------|---------------------------------|
| Constant Service Temp. | -55 to 80 °C [-67 to 176 °F] |
| Storage Temperature of Unmixed Parts | 5 to 22 °C [41 to 72 °F] |

Principal Components

Name

Ethyl-2-cyanoacrylate

CAS Number

7085-85-0

Properties of Cured 8334

| Physical Properties | Method | Value |
|--|------------------------|---|
| Color | Visual | Clear |
| Density @25 °C [79 °C] | | 1.05 g/cm ³ |
| Lap Shear Strength | ISO 4587 ^{b)} | |
| (Stainless Steel) | <30 s fixture time | >14.5 N/mm ² [$>2\ 100\ \text{lb/in}^2$] |
| (Aluminum) | <25 s fixture time | >12.1 N/mm ² [$>1\ 750\ \text{lb/in}^2$] |
| (ABS) | <20 s fixture time | >6.2 N/mm ² [$>900\ \text{lb/in}^2$] |
| (PVC) | <15 s fixture time | >6.2 N/mm ² [$>900\ \text{lb/in}^2$] |
| (Polycarbonate) | <30 s fixture time | >6.2 N/mm ² [$>900\ \text{lb/in}^2$] |
| (Phenolic Rubber) | <25 s fixture time | >6.2 N/mm ² [$>900\ \text{lb/in}^2$] |
| (Neoprene) | <10 s fixture time | >5.2 N/mm ² [$>750\ \text{lb/in}^2$] |
| Butt Joints Tensile Strength (Stainless Steel) | ISO 6922 | >12.4 N/mm ² [$>1\ 800\ \text{lb/in}^2$] |
| Electrical Properties | Method | Value |
| Volume Resistivity | ASTM D 257 | $\geq 2 \times 10^{15}\ \Omega\cdot\text{cm}$ |
| Dielectric Dissipation & Constant @1 kHz | ASTM D 150-98 | dissipation, <i>D</i> constant, <i>k'</i> 0.02 2 to 3.5 |

Note: Specifications are for sample cured at 50% relative humidity for at least 24 hours.

a) N/mm² = MPa; lb/in² = psi

b) The fixture time is the time required to develop a shear strength of 0.1 N/mm². This corresponds to the strength at which the parts may no longer be moved independently.

Storage

Store between 5 °C to 22 °C [41 and 72 °F] in a dry area away from sunlight.

Compatibility

Adhesion—As seen in the substrate adhesion table, the 8334 adheres to a wide variety of materials.

Materials Subject to Bonding

| <i>Natural</i> | <i>Plastics/Polymers</i> | <i>Ceramics</i> | <i>Metals</i> |
|--|--|-----------------|--|
| Latex Leather Paper, Fiber Fabric Rubber Wood | ABS Acrylic Bakelite EPDM Fiberglass NBR (nitrile rubber) Neoprene Nitrile Phenolic Polybutylene Terephthalate Polycarbonate Polyester PVC Styrene-Butadiene rubber | Porcelain | Aluminum Brass Chrome Copper Steel |

Note: The MG 8334 Super Glue is not compatible with contaminants like oil, and greases that may affect adhesion. If contamination is present, clean the surface with a suitable cleaner such as MG Chemicals 4050 Safety Wash, 406B Superwash, or 824 Isopropyl Alcohol.

Chemical Resistance—To test the chemical resistance, the adhesive was aged in various chemicals and the strength of the adhesive bond was compared to that of control specimens.

Retained Adhesive Strength and After Chemical/Solvent Exposure

| <i>Chemical/Solvent</i> | <i>Conditions/Temperature (°C)</i> | <i>Exposure Duration (hour)</i> | <i>Percent of Initial Strength</i> |
|-------------------------|------------------------------------|---------------------------------|------------------------------------|
| Gasoline | 22 °C | 500 | 100% |
| Isopropanol | 22 °C | 500 | 100% |
| Ethanol | 22 °C | 500 | 100% |
| Freon | 22 °C | 500 | 100% |
| Motor Oil | 40 °C | 500 | 100% |
| Polycarbonate | 40 °C @95% RH | 500 | 100% |

To remove the 8334 adhesive, you can use acetone.

Health, Safety, and Environmental Awareness

Please see the 8334 **Safety Data Sheet** (SDS) for details on transportation, storage, handling and other security guidelines.


Health and Safety: DANGER: Hazardous Adhesive

Do not get in eyes, on skin, or clothing. Do not breathe vapor. Use with adequate ventilation. Do not use near sparks, heat, or open flames. Contact will result in rapid bonding of tissues and may bond skin-to-skin or to other materials. The cured adhesive presents no known hazard.

HMIS® RATING

| | |
|-----------------------------|------------|
| HEALTH: | * 2 |
| FLAMMABILITY: | 2 |
| PHYSICAL HAZARD: | 1 |
| PERSONAL PROTECTION: | |

NFPA® 704 CODES



Approximate HMIS and NFPA Risk Ratings Legend:

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

Application Instructions

For best results, follow the procedure below.

To bond surfaces

1. Clean the surface to be bonded and let dry.
2. Remove cap.
3. Apply the adhesive directly on the surface and immediately hold the surface together for at least 25 seconds until the adhesive has fixtured.

NOTE: Remember to recap the syringe promptly after use.

TIP: Wiping the surface with a damp cloth prior to application can promote bonding.

Packaging and Supporting Products

| <i>Cat. No.</i> | <i>Packaging</i> | <i>Net Volume</i> | | <i>Shipping Weight</i> | |
|-----------------|------------------|-------------------|------------|------------------------|------|
| 8334-3G | Tube | 50 mL | 1.69 fl.oz | 0.46 kg ^{a)} | 1 lb |

a) Pack of twenty-four

Technical Support

Contact us regarding any questions, suggestions for improvements, or problems with this product. Application notes, instructions and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)
+(1) 905-331-1396 (International)
+(44) 1663 362888 (UK & Europe)
Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: **Manufacturing & Support**
1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office
9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Warranty

M.G. Chemicals Ltd. warrants this product for 12 months from the date of purchase by the end user. *M.G. Chemicals Ltd.* makes no claims as to shelf life of this product for the warranty. The liability of *M.G. Chemicals Ltd.* whether based on its warranty, contracts, or otherwise, shall in no case include incidental or consequential damage.

Disclaimer

This information is believed to be accurate. It is intended for professional end users who have the skills required to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный)

Факс: 8 (812) 320-02-42

Электронная почта: org@eplast1.ru

Адрес: 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.