Technical Data				May, 2010
Product Description	STIPLION 3M TM Scotch-Weld TM Urethane Adhesives DP605 NS Off-White and DP640 Brown are two-part, non-sag urethane adhesives. They feature tough, flexible bonds with good adhesion to a wide variety of substrates, especially wood and many properly abraded and cleaned plastics. Good adhesion can also be obtained on etched aluminum as well as primed aluminum, steel and glass. For maximum bond durability under moisture conditions, priming of glass and metal substrates is required.			
	Off-White B/A or 3M TM Sco	otch-Weld [™] U	Irethane Adhesive 354	9 B/A.
Features	 Tough, flexible bonds Non-Sag/Thixotropic 1:1 Mix Ratio 	5 orBonLowUres	40 minute worklife ds wood and many pla v halogen content (3M thane Adhesive DP60	stics ™ Scotch-Weld™ 5 NS)
Typical Uncured Physical Properties	Note: The following technica or typical only and sho	l information a ould not be used	nd data should be consi l for specification purpo	idered representative oses.
	Product		Scotch-Weld Urethane Adhesive DP605 NS Off-White	Scotch-Weld Urethane Adhesive DP640 Brown
	Color		Off-White	Brown
	Base Resin		Polyol/Isocyanate	Polyol/Isocyanate
	Mix Ratio (B:A)	Volume Weight	1:1 1:1.08	1:1 1:1.09
	Net Weight Lbs./Gal.	Base Accelerator	8.8-9.2 9.7-10.2	10.1-10.5 11.1-11.5
	Viscosity ^{1a} (Approx.) time to deliver 20 gms @ 20 psi thru a .104 orifice @ 75°F (24°C) second	Base Accelerator ds.	11-20 11-20	
	Viscosity ^{1b} Brookfield RVF @ 10 rpm	Base (#6 Spindle)	_	10,000-40,000
	cps @ 75°F (24°C)	Accelerator (#5 Spindle)	_	15,000-55,000

 Viscosity determined using 3M test method C-1019. Procedure involves pressure flowmeter, .104 orifice sample cup, pressure of 20 psi and temperature of 75°F ± 2°F (24°C ± -16°C).

1b. Viscosity determined using C-1D. Procedure involves using a RVF Brookfield viscometer with either a #6 or #5 spindle at 10 rpm.

Typical CuredNote:The following technicThermal Propertiesor typical only and size

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Product	3M™ Scotch-Weld™ Urethane Adhesive DP605 NS Off-White	3M™ Scotch-Weld™ Urethane Adhesive DP640 Brown
Physical:		
Color	Off-White	Brown
Shore A Hardness (ASTM D 2240)	75-85	70-80
Time to Handling Strength ²	15-20 min. @ 23°C (73°F)	6-8 hrs. @ 23°C (73°F)
Cure Time ³	48 hours @ 23°C (73°F)	7 days @ 23°C (73°F)
Elongation ⁴	100%	100%

Electrical:	Scotch-Weld Urethane Adhesive DP605 NS Off-White	Scotch-Weld Urethane Adhesive DP640 Brown
Dielectric Constant (ASTM D 150)	3.1 @ 1 KHz @ 23°C	5.9 @ 1 KHz @ 23°C
Dissipation Factor (ASTM D 150)	.021 @ 1 KHz @ 23°C	.12 @ 1 KHz @ 23°C
Dielectric Strength (ASTM D 149)	640 volts/mil	470 volts/mil
Volume Resistivity (ASTM D 257)	1.0 x 10 ¹⁴ ohm-cm	2.6 x 10 ¹² ohm-cm

Thermal:	Scotch-Weld Urethane Adhesive DP605 NS Off-White	Scotch-Weld Urethane Adhesive DP640 Brown
Wt. loss by Thermal⁵ Gravimetric Analysis	5% @ 300°C	_
Coefficient of Thermal ⁶ Expansion (in./in./°C)	121 x 10 ⁻⁶ below 41°C 219 x 10 ⁻⁶ above 41°C	
Thermal Conductivity ⁷ (btu-ft./sq. fthr. °F)	0.101 @ 45°C	_
Glass Transition Temp ⁸	41°C	_

2. Handling strength determined per 3M test method C-3179. Time to handling strength taken to be that time required to achieve 50 psi OLS strength using aluminum substrates.

3. The cure time is defined as that time required for the adhesive to achieve a minimum of 80% of the ultimate strength as measured by aluminum - aluminum OLS.

4. Elongation is determined using 3M test method C-3094/ASTM D 882.

 Weight loss by TGA reported as that temperature at which 5% weight loss occurs by TGA in air at 5°C rise per minute per ASTM 1131-86.

6. TCE determined with TMA Analyzer using a heating rate of 50°F (10°C) per minute. Second heat values given.

7. Thermal conductivity determined using ASTM C177 and C-matic Instrument with 2" diameter samples.

8. Glass transition temperature (Tg) determined using DSC Analyzer with a heating rate of 68°F (20°C) per minute. Second heat values given.

Typical Cured Thermal Properties (continued)	Note: The following technical info or typical only and should n	rmation and data should be ot be used for specification	e considered representative purposes.
	Solvent Resistance: ⁹ Results for 3M [™] Scotch-Weld [™] Urethane Adhesive DP605 NS Off-White only.		
	(Visual check after immersion in s	specified solvent at 23°C [73	°F])
		1 Hour	1 Month
	Acetone	А	В
	Isopropyl Alcohol	А	А
	Freon [®] TF	А	A
	Freon [®] TMC	В	С
	1,1,1-Trichloroethane	А	В
	RMA Flux	А	А
	Key: A-Unaffected; B-Sight	Attack; C-Moderate/Seve	ere Attack

9. Solvent resistance was determined using cured (24 hrs RT + 2 hrs 160°F [71°C]) samples (1/2" x 4" x 1/8" thickness) immersed in the test solvent for 1 hour and 1 month. After the allotted period of time the sample was removed and visually examined for surface attack as compared to the control.

Key: A - Unaffected - no change to color or surface texture.

B - Slight attack - noticeable swelling of surface.

C - Moderate/severe attack - extreme swelling of surface.

3MTM Scotch-WeldTM Urethane Adhesive DP605 NS can be considered "low halogen". Low halogen is defined by the Electrotechnical Commission (IEC) 61249-2-21 standard as having less than 900 ppm chlorine, 900 ppm bromine, and less than 1500 ppm total chlorine and bromine.

3MTM Scotch-WeldTM Urethane Adhesive DP605 NS Test Results

Halogens (determined by ion chromatography)

Total Chlorine (ppm)	Total Bromine (ppm)	Total Halogens (ppm)
670	< 10	< 800

Typical Adhesive Performance	Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.
Characteristics	The following product performance data were obtained in the 3M laboratory under the conditions specified. The following data shows typical results obtained with

the conditions specified. The following data shows typical results obtained with 3MTM Scotch-WeldTM Urethane Adhesives DP605 NS Off-White and DP640 Brown when applied to properly prepared substrates, cured for 7 days at 73°F (23°C) under 2 psi cure pressure, and tested according to the test methods indicated.

Overlap Shear

Overlap shear bonds were tested on 1" wide test specimens with a 1/2" overlap of the adhesive bonded area. Substrates were bonded after surfaces were prepared according to the surface preparation section. They were cured for 1 week at 73°F (23°C) prior to testing. Tests were run according to Test Method ASTM D1002-72.

				OLS	(psi)
Substrate	Substrate Thickness (in.)	Bondline Thickness (in.)	S Test Temperature (°F)	3M [™] Scotch-Weld™ Urethane Adhesive DP605 NS Off-White	3M™ Scotch-Weld™ Urethane Adhesive DP640 Brown
CRS/CRS .035 .005 73 (23°C) 1350 2000 CRS/CRS .035 .005 180 (82°C) 140 300 Al/Al .063 .005 73 (23°C) 1460 2000 EPDM/Wood .250/.125 .005 73 (23°C) 100 SBR/Wood .250/.125 .005 73 (23°C) 100 + SF* PC/PC .125 .005 73 (23°C) 100 + SF* PC/PC .125 .005 73 (23°C) 640 1850* PVC/PVC .125 .005 73 (23°C) 550 950* FRP/FRP .125 .005 73 (23°C) 1180 1150* CRS - cold rolled steel Al - aluminum EPDM - ethylene propylene diene monomer SBR - styrene butadiene rubber PC - polycarbonate PVC - polycarbonate PVC - polyvinyl chloride FRP - fiberglass reinforced plastic *Substrate Failure *Substrate Failure					
Bondline Thickness Study (Tested according to ASTM D 1002-72) OLS (psi)					
Substrate	Substrate Thickness (in.	Bondline) Thickness (in	Test n.) Temperature	3M™S Uretha (°F) DP605	cotch-weid M ine Adhesive NS Off-White
CRS/CRS CRS/CRS CRS/CRS CRS/CRS	.035 .035 .035 .035	.005 .010 .015 .020	73 (23°C) 73 (23°C) 73 (23°C) 73 (23°C) 73 (23°C))))	1350 1150 1050 850

Typical Adhesive
PerformanceNote: The following technical information and data should be considered representative
or typical only and should not be used for specification purposes.Characteristics
(continued)Peel Strength

Peel strength tests were run on 1" wide specimens that were aged for 1 week at 73°F (21°C). The 180° peel testing was run according to Test Method ASTM D1876-61T. Substrates were prepared according to the surface preparation section.

Substrate	Substrate Thickness (in.)	Bondline Thickness (in.)	Test Temperature (°F)	Peel Strength (piw) 3M™ Scotch-Weld™ Urethane Adhesive DP605 NS Off-White
CRS/CRS	.022	.005	73 (23°C)	13
	.022	.015	73 (23°C)	18
CRS/CRS	.035	.005	73 (23°C)	36
	.035	.015	73 (23°C)	47
AI/AI	.022	.005	73 (23°C)	17

3MTM EPXTM Pneumatic Applicator Delivery Rates

50 ml Applicator – Maximum Pressure 50 psi

Adhesive*	1/4 in. Nozzle gms/minute
3M [™] Scotch-Weld [™] Urethane Adhesive DP605 NS Off-White	68.5
3M [™] Scotch-Weld [™] Urethane Adhesive DP640 Brown	44.7

*Tests were run at a temperature of 70°F ± 2°F (21°C ± 1°C) and at maximum applicator pressure.

Handling/Curing Information

Directions for Use

- 1. For optimum strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental aging resistance desired by the user. For suggested surface preparations on common substrates, see the section on surface preparation.
- 2. These products consist of two parts.

Mixing:

For Duo-Pak Cartridges - 50 ml

Remove the Scotch-Weld urethane adhesive DP605 NS Off-White or DP640 Brown duo-pak cartridge from its foil package and place it into the 3MTM EPX Applicator. Remove the cap and dispense a small amount of adhesive to equalize piston displacement and to assure that no material is blocking either the base or accelerator ports. Attach the mixing nozzle to the duo-pak cartridge and apply the adhesive to clean surfaces. To store a partially used duo-pak cartridge leave mixing nozzle in place and replace after storage. **Note:** Scotch-Weld urethane adhesive DP605 NS Off-White is sensitive to moisture. For best results, use the entire contents of the cartridge within a few weeks after removing the cartridge from the sealed foil pack. If extended storage is necessary, the duo-pak cartridge should be stored in a sealed plastic bag. For hand mixing, expel the desired amount of adhesives and mix thoroughly (10-15 seconds after uniform color is obtained).

Handling/Curing Information (<i>continued</i>)	For Duo-Pak Cartridges - 200/400 ml
	Directions for Use: While holding cartridge in an upright position, remove insert from duo-pak cartridge by unscrewing plastic nut. Detach metal removal disc from insert to free plastic nut nozzle attachment. Clear orifices if necessary. Attach mixing nozzle and secure with plastic nut. Place cartridge into 3M TM EPX Applicator. Discard a small quantity of dispensed adhesive to assure both components are dispensing equally. Apply adhesive to clean surfaces, join parts, secure until set up (15 minutes @ 75°F (24°C) for 3M TM Scotch-Weld TM Urethane Adhesive DP605 NS Off-White, 6-8 hours for 3M TM Scotch-Weld TM Urethane Adhesive DP640 Brown @ 75°F (24°C). Leave nozzle attached to store. Replace nozzle after storage.
	For Bulk Containers
	Mix thoroughly by weight or volume in the ratios specified in the typical uncured properties section. Resulting color should be uniform. After opening, containers of adhesive should be used completely. If storage of partially used containers is necessary, flush each container with dry nitrogen just before sealing the containers.
	4. Application to the substrates should be made within 5 minutes for Scotch-Weld urethane adhesive DP605 NS Off-White or 40 minutes for Scotch-Weld urethane adhesive DP640 Brown. Larger quantities and/or higher temperatures will reduce this working time.
	 Join the adhesive coated surfaces and allow to cure at 60°F (16°C) or above until firm. Heat up to 200°F (93°C) will speed curing.
	 Scotch-Weld urethane adhesive DP605 NS Off-White will fully cure in 48 hours @ 75°F (24°C). Scotch-Weld urethane adhesive DP640 Brown will fully cure in 7 days 75°F (24°C).
	7. Keep parts from moving during cure. Contact pressure is necessary. Maximum shear strength is obtained with a 3-5 mil bond line.
	8. Excess uncured adhesive can be cleaned up with ketone type solvents.*
	*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.
	Adhesive coverage (typical): A 0.005 in. thick bondline will yield a coverage of 320 sq. ft./gallon.
Application Equipment Suggestions	For small or intermittent applications, the 3M EPX applicator is a convenient method of application.
	For larger applications, these products may be applied by use of flow equipment.
	Two-part mixing/proportioning/dispensing equipment is available for intermittent or production line use. These systems may be desirable because of their variable shot size and flow rate characteristics and are adaptable to many applications.

Surface Preparation	For optimum strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental aging resistance desired by the user.			
	The following cleaning methods are suggested for common surfaces:			
	Steel:			
	1. Wipe free of dust with oil-free solvent such as acetone or isopropyl alcohol.*			
	2. Sandblast or abrade using clean fine grit abrasives (150 grit or finer).			
	3. Wipe again with solvent to remove loose particles.			
	4. If a primer is used, it should be applied within 4 hours after surface preparation.			
	Aluminum:			
	 Alkaline Degrease: Oakite 164 solution (9-10 oz./gallon water) at 190°F ± 10°F (88°C ± -23°C) for 10-20 minutes. Rinse immediately in large quantities of cold running water. 			
	2. Acid Etch: Place panels in the following solution for 10 minutes at $150^{\circ}F \pm 5^{\circ}F$ (66°C ± -20°C).			
	Sodium Dichromate4.1 - 4.9 oz./gallonSulfuric Acid, 66°Be38.5 - 41.5 oz./gallon2024-T3 aluminum (dissolved)0.2 oz./gallon minimumTap Water as needed to balance10.2 oz./gallon minimum			
	3. Rinse: Rinse panels in clear running tap water.			
	4. Dry: Air dry 15 minutes; force dry 10 minutes at $150 \pm 10^{\circ}$ F (66°C ± -20°C).			
	5. If primer is to be used, it should be applied within 4 hours after surface preparation.			
	Plastics/Rubber:			
	1. Wipe with isopropyl alcohol.*			
	2. Abrade using fine grit abrasives (150 grit or finer).*			
	3. Wipe with isopropyl alcohol.*			
	Glass:			
	1. Solvent wipe surface using acetone or MEK.*			
	 Apply a thin coating (0.0001 in. or less) of 3M[™] Scotch-Weld[™] Metal Primer EC3901 to the glass surfaces to be bonded and allow the primer to dry 60 minutes at room temperature before bonding. 			
	*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.			

Storage	Store products at 60-80°F (16-27°C) for maximum storage life. Rotate stock on a "first-in first-out" basis.
Shelf Life	When stored in the original, unopened container at the storage conditions suggested, these products have a shelf life of 12 months from date of shipment.
Precautionary Information	Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.
Technical Information	The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.
Product Use	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.
Warranty, Limited Remedy, and Disclaimer	Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.
Limitation of Liability	Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.
	This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.

ЗМ

Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06 St. Paul, MN 55144-1000 800-362-3550 • 877-369-2923 (Fax) www.3M.com/industrial



Recycled Paper 40% pre-consumer 10% post-consumer 3M and Scotch-Weld are trademarks of 3M Company. Freon is a registered trademark of E.I. DuPont de Nernours Co. Printed in U.S.A. ©3M 2010 78-6900-7083-0 (5/10)



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный) **Факс:** 8 (812) 320-02-42 **Электронная почта:** <u>org@eplast1.ru</u> **Адрес:** 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.