



# BERGQUIST HI FLOW THF 1600G

Known as BERGQUIST HI-FLOW 300G  
November 2018

## PRODUCT DESCRIPTION

Fiberglass-Reinforced, Phase Change Thermal Interface Material.

<b>Technology</b>	Silicone
<b>Appearance</b>	Green
<b>Reinforcement Carrier</b>	Fiberglass
<b>Total Thickness</b> , ASTM D374	0.127mm
<b>Application</b>	Thermal management, Thermally conductive adhesive
<b>Operating Temperature</b>	100 °C

## FEATURES AND BENEFITS

- Thermal impedance: 0.2°C-in<sup>2</sup>/W @ 25 psi
- Will not drip or run like grease
- Phase change compound coated on a fiberglass carrier

## TYPICAL APPLICATIONS

- Computer and peripherals
- As a thermal interface where bare die is exposed and needs to be heat sinked

BERGQUIST HI FLOW THF 1600G consists of a thermally conductive 55°C phase change compound coated on a fiberglass web. BERGQUIST HI FLOW THF 1600G is designed as a thermal interface material between a computer processor and a heat sink.

Above the phase change temperature, BERGQUIST HI FLOW THF 1600G wets-out the thermal interface surfaces and flows to produce low thermal impedance. The material requires pressure of the assembly to cause flow. BERGQUIST HI FLOW THF 1600G will not drip or run like grease.

## TYPICAL PROPERTIES

### Physical Properties

Elongation , 45° to warp and fill, ASTM D882A, %	40
Tensile Strength, ASTM D882A, MPa	3
Phase Change Temperature, ASTM D3418, °C	55
Flammability Rating, UL 94	V-0

### Electrical Properties

Dielectric Breakdown Voltage , ASTM D149, Vac	300
Dielectric Constant , ASTM D150 @ 1,000 Hz	3.5
Volume Resistivity, ASTM D257, ohm-meter	1×10 <sup>8</sup>

### Thermal Properties

Thermal Conductivity , ASTM D5470, W/(m-K) <sup>(1)</sup>	1.6
---	-----

## Thermal Performance vs. Pressure

TO-220 Thermal Performance, °C/W:

@ 10 psi	0.96
@ 25 psi	0.92
@ 50 psi	0.88
@ 100 psi	0.85
@ 200 psi	0.84

Thermal Impedance, ASTM D5470, °C-in<sup>2</sup>/W <sup>(2)</sup>:

@ 10 psi	0.27
@ 25 psi	0.2
@ 50 psi	0.16
@ 100 psi	0.15
@ 200 psi	0.14

1) This is the measured thermal conductivity of the Hi-Flow coating. It represents one conducting layer in a three-layer laminate. The Hi-Flow coatings are phase change compounds. These layers will respond to heat and pressure induced stresses. The overall conductivity of the material in post-phase change, thin film products is highly dependent upon the heat and pressure applied. This characteristic is not accounted for in ASTM D5470. Please contact Bergquist Product Management if additional specifications are required.

2) The ASTM D5470 test fixture was used and the test sample was conditioned at 70°C prior to test. The recorded value includes interfacial thermal resistance. These values are provided for reference only. Actual application performance is directly related to the surface roughness, flatness and pressure applied.

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

## Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

## APPLICATION METHODS

1. Hand-apply to 40°- 50°C heat sink. The heat sink is heated in an oven or by a heat gun to between 40°- 50°C allowing the BERGQUIST HI FLOW THF 1600G pad to be applied like an adhesive pad. The heat sink is then cooled to room temperature and packaged.

2. Hand-apply to 20°- 35°C heat sink. BERGQUIST HI FLOW THF 1600G can be applied to a room temperature heat sink with the assistance of a foam roller. The pad is positioned on the heat sink and a hand roller is used to apply pressure of 30 psi.

3. Automated equipment with 30 psi pressure. A pick-and-place automated dispensing unit can be used to apply BERGQUIST HI FLOW THF 1600G to a room temperature heat sink. The placement head should have a soft silicone



rubber pad, and apply 30 psi pressure to the pad on transfer to the 20°- 35°C heat sink.

more United States or foreign patents or patent applications.

**Trademark usage:** [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

## CONFIGURATIONS AVAILABLE

BERGQUIST HI FLOW THF 1600G are supplied in:

- Sheet form, roll form and die-cut parts
- With or without pressure-sensitive adhesive

Reference 1

## Conversions

$$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$$

$$\text{kV/mm} \times 25.4 = \text{V/mil}$$

$$\text{mm} / 25.4 = \text{inches}$$

$$\text{N} \times 0.225 = \text{lb}$$

$$\text{N/mm} \times 5.71 = \text{lb/in}$$

$$\text{psi} \times 145 = \text{N/mm}^2$$

$$\text{MPa} = \text{N/mm}^2$$

$$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$$

$$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$$

$$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$$

$$\text{mPa}\cdot\text{s} = \text{cP}$$

## Disclaimer

### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



#### Как с нами связаться

**Телефон:** 8 (812) 309 58 32 (многоканальный)

**Факс:** 8 (812) 320-02-42

**Электронная почта:** [org@eplast1.ru](mailto:org@eplast1.ru)

**Адрес:** 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.