

## Description

Our 419C *Acrylic Conformal Coating* is an IPC-CC-830B and UL 94-V0 certified, fast drying, xylene and toluene free product that provides an excellent finish. This one part coating is easy to use and does not require special or costly equipments to apply. It is ideal for high moisture environments and applications requiring easy repair and rework.

The 419C coating protects electric circuits against moisture, dirt, dust, and thermal shocks that could corrode, short circuit, or otherwise damage the electric components. It insulates against high-voltage arcing, shorts, and static discharges. As well, this coating provides a high dielectric withstand voltage that allows traces to be put closer together helping with miniaturization.

## Applications & Usages

The 419C coating improves reliability, operational range, and lengthens the life of electrical and electronic components and assemblies. Its primary applications are in the automobile, marine, aerospace, aviation, communication, instrumentation, industrial control equipment, and consumer electronics industries.

Common acrylic conformal coatings uses are with electric generators, motors, transformers, relays, and air bag controllers. The 419C coating can serve to protect high technology devices like cell phones, computer tablets, avionics, and more.

## Benefits and Features

- **Certified *UL 94V-0*** (File # [E203094](#))
- **Externally Qualified** to *IPC-CC-830B* by Pacific Testing Laboratories
- **Super fast cure**—tack free in about 3 min; full cure in <30 min at 65 °C [149 °F]
- **Protects electronics from** moisture, corrosion, fungus, and static discharges
- **No Hazardous Air Pollutants**—free of toluene or xylene • VOC of only 67% • free of ozone depletion compounds • coating is RoHS compliant
- **Excellent finish**—smooth, homogeneous, and durable crystal clear coat
- **Easy to inspect**—fluoresces under UV light
- **Easy rework and repairs**—can solder through coat • removable with Cat. No. 435 thinner or Cat. No. 8310 stripper

## Curing & Work Schedule

| Properties                              | Value       |
|---|-------------|
| Tack Free                               | 3-5 minutes |
| Recoat Time                             | 2 minutes   |
| Full Cure <sup>a)</sup> @25 °C [77 °F]  | 24 hours    |
| Full Cure <sup>a)</sup> @65 °C [149 °F] | 30 minutes  |

a) Cure times assume a minimum thickness of 1 mil and standard conditions.

## Service Ranges

| Properties   | Value   |
|--|---|
| Service Temperature                                    | -65 to +125 °C<br>[-85 to +257 °F]                  |
| Max Coverage <sup>b)</sup> per 1L<br>for 25 µm [1 mil] | <63 000 cm <sup>2</sup><br>[<67.8 ft <sup>2</sup> ] |

b) Estimated based on ideal values. Actual value will be somewhat less than quoted.

## Chemical Components

| Name               | CAS Number  |
|--------------------|-------------|
| Acrylic Resin      | proprietary |
| Ethyl Acetate      | 141-78-6    |
| Acetone            | 67-64-1     |
| N-Heptane          | 142-82-5    |
| PM Acetate [PGMEA] | 108-65-6    |

## Properties of Cured 419C

| <i>Physical Properties</i>                | <i>Method</i>           | <i>Value</i>                                      |
|---|-------------------------|---|
| Color                                     | Visual                  | Crystal Clear                                     |
| Solderability                             | —                       | Excellent   |
| Weather Resistance                        | —                       | Excellent   |
| Fungus Resistance                         | IPC-TM-650 2.6.1.1      | Excellent   |
| Flexibility                               | IPC-TM-650 2.4.5.1      | Excellent   |
| Flammability                              | UL registered           | 94V-0   |
| <i>Electric Properties</i>                | <i>Method</i>           | <i>Value</i>                                      |
| Dielectric Withstand Voltage              | per IPC-TM-650          | >1500 V   |
| Insulation Resistance<br>(after 24 hours) | IPC-TM-650 Test 2.6.3.4 | 5x10 <sup>12</sup> Ω                              |
| <i>Environmental &amp; Ageing Study</i>   | <i>Method</i>           | <i>Value</i>                                      |
| Salt Spray Test: 7 day @35 °C +Salt/Fog   | ASTM B117-2011          | 5B = 0% area removed<br>None<br>No change<br>None |
| Cross-hatch adhesion                      | ASTM D3359-2009         |   |
| Cracking, unwashed area                   | ASTM D661-93            |   |
| Visual Color, unwashed area               | ASTM D1729-96           |   |
| Peeling, unwashed area                    | ASTM D1729-96           |   |

Note: See Appendix A for UL 94V-0 and IPC-CC-830B standards test results.

## Properties of Uncured 419C

| <i>Physical Property</i>   | <i>Method</i>  | <i>Value</i>                   |
|----------------------------|----------------|--------------------------------|
| Odor                       | —              | Ether-like, gasoline and minty |
| Viscosity at 23 °C [73 °F] | Brookfield SP1 | 7.2 cP [0.0072 Pa·s]           |
| Density                    | MIL-STD-45662A | 0.874 g/ml                     |
| Flash Point                | Closed Cup     | -19 °C [-2.2 °F]               |
| Boiling Point              |                | ≥66 °C [≥150 °F]               |
| Solids Content (w/w)       |                | 16.7%                          |

## Compatibility

The 419C acrylic coating is compatible with most materials found on printed circuit assemblies; however, in an uncured state it is not compatible with contaminants like water, oil, and greasy flux residues. Therefore, it is extremely important to clean the printed circuit assembly thoroughly with a suitable electronic cleaner before applying the coating.

The chosen electronic cleaner should remove moisture, wax, greases, oils, and all other contaminants that are known to cause defects in this type of conformal coating. (See recommended cleaners on page 5.)

## Health, Safety, and Environmental Awareness

Please see the 419C-Liquid **Material Safety Data Sheet** (MSDS) for more details on transportation, storage, handling and other security guidelines.

**Environmental Impact:** The 419C formulation is designed to be environmentally friendly. It is free from ozone depletion compounds or toxic solvents. It has a lower volatile organic content of 67.0% (w/w) [or 581 g/L] than the older 419B formulation. After dilution with 435 Thinner Cleaner, the regulated VOC drops to 38.8% (~350 g/L). The coating is RoHS compliant.

**Health and Safety:** The aerosol is flammable and should be kept away from flames and other ignition sources. As with most paint materials, avoid breathing in fumes or direct contact with the material. Solvents therein can cause irritation and other symptoms like headaches, pain, as well as having long term exposure effects.


Wear safety glasses and disposable gloves. Wash hands thoroughly after use. Use in the open air, in fume hoods, or in well ventilated area. For short or long term (8 hours) at levels of exposures exceeding 500 ppm n-heptane or 750 ppm acetone, use NIOSH approved respirator with organic vapor cartridges rated for this order of concentrations.

The cured coating presents no known hazard.

### HMIS® RATING

|                             |          |
|-----------------------------|----------|
| <b>HEALTH:</b>              | <b>2</b> |
| <b>FLAMMABILITY:</b>        | <b>3</b> |
| <b>PHYSICAL HAZARD:</b>     | <b>0</b> |
| <b>PERSONAL PROTECTION:</b> |          |

### NFPA® 704 CODES



*Approximate HMIS and NFPA Risk Ratings Legend:*

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

## Spray Gun Application Instructions

Follow the procedure below for best results.

### To apply the required thickness by weight

1. Mix thoroughly, and spray a test pattern. This step ensures good flow quality and helps establish appropriate distance to avoid runs.
2. At a distance of 20 to 25 cm (8 to 10 inches), hold the gun at around 45°, and spray a thin and even coat onto the horizontal board. For best results, use spray-and-release strokes with an even motion to avoid excess paint in one spot.
3. Before the next coat, rotate the board 90° to ensure good coverage.
4. Wait at least 2 minutes, and spray another coat. The delay avoids trapping solvent between coats.
5. Apply other coats until desired thickness is achieved. (Go to Step 3)
6. Let dry for 3-5 minutes (flash off time) at room temperature.

### To cure the conformal coating

Full cure can be achieved in less than 30 minutes by using an infrared lamp or in convection oven at 65 °C [149 °F]. At room temperature, the coat dries to the touch in 3-5 minutes. And full cure takes about 24 hours.

The procedure above is based on a minimum thickness of 25 µm (1 mil) conformal coating. After full cure, measure the actual conformal coating thickness to ensure it meets the applications requirements.

## Packaging and Supporting Products

### Product Availability

| Cat. No.         | Form    | Net Volume       | Net Weight      | Shipping Weight                    |
|------------------|---------|------------------|-----------------|------------------------------------|
| <b>419C-340G</b> | Aerosol | 220 mL 7.2 fl oz | 340 g 12 oz     | 4.8 kg 10.5 lb (×10) <sup>a)</sup> |
| <b>419C-55ML</b> | Liquid  | 55 mL 1.9 fl oz  | 50 g 1.6 oz     | 1.0 kg 2.1 lb (×5) <sup>b)</sup>   |
| <b>419C-1L</b>   | Liquid  | 950 mL 1 qt      | 0.8 kg 1.8 lb   | 5.5 kg 11.5 lb (×5) <sup>b)</sup>  |
| <b>419C-4L</b>   | Liquid  | 3.8 L 1 gal      | 3.3 kg 7.3 lb   | 3.8 kg 8.3 lb                      |
| <b>419C-20L</b>  | Liquid  | 19 L 5 gal       | 16.6 kg 36.5 lb | 19 kg 42 lb                        |

Contact MG Chemicals if custom packaging or sizes are required

a) Pack of ten cans

b) Pack of five bottles

### Thinners & Conformal Coating Removers

- Cat. No. 435-55ML (2 oz), 435-1L (33 oz), 435-4L (1 gal) Conformal Coating Thinner
- Cat. No. 8310-100ML Conformal Coating Stripper



ISO 9001 Registered Quality System.  
Burlington, Ontario, Canada QMI File # 004008

# Acrylic Conformal Coating 419C Technical Data Sheet

419C-Liquid

## Electronic Cleaners

- Cat. No. 4050A-340G, 4050-1L, 4050-4L, 4050-20L Safety Wash Electronics Cleaner
- Cat. No. 406B-450G Superwash Cleaner Degreaser
- Cat. No. 824 Isopropyl Alcohol

## Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at [www.mgchemicals.com](http://www.mgchemicals.com).

Email: [support@mgchemicals.com](mailto:support@mgchemicals.com)

Phone: 1-800-340-0772 Ext. 130 (Canada, Mexico & USA)  
1-905-331-1396 Ext. 130 (International)

Fax: 1-905-331-2862 or 1-800-340-0773

Mailing address: **Manufacturing & Support**  
1210 Corporate Drive  
Burlington, Ontario, Canada  
L7L 5R6

**Head Office**  
9347-193rd Street  
Surrey, British Columbia, Canada  
V4N 4E7

## Warranty

*M.G. Chemicals Ltd.* warrants this product for 12 months from the date of purchase by the end user. *M.G. Chemicals Ltd.* makes no claims as to shelf life of this product for the warranty. The liability of *M.G. Chemicals Ltd.* whether based on its warranty, contracts, or otherwise shall in no case include incidental or consequential damage.

## Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

## Appendix A

### Standards Qualification

Certified UL 94V-0 and IPC-CC-830B qualified.

| <i>Qualification Criteria</i>      | <i>Test Method</i>                       | <i>Results</i> |
|------------------------------------|--|----------------|
| <b>UL 94V-0</b>                    |  |                |
| Coating flammability               | UL 94V (File # <a href="#">E203094</a> ) | 94V-0          |
| <b>Qualified IPC-CC-830B*</b>      |  |                |
| Appearance                         | IPC-CC-830B 3.5.2                        | pass           |
| Fluorescence                       | IPC-CC-830B 3.5.3                        | pass           |
| Flammability                       | IPC-CC-830B 3.5.6                        | pass           |
| Fungus Resistance                  | IPC-TM-650 2.6.1.1                       | pass           |
| Flexibility                        | IPC-TM-650 2.4.5.1                       | pass           |
| Dielectric Withstand Voltage       | IPC-TM-650 2.5.7.1                       | pass           |
| Moisture and Insulation Resistance | IPC-TM-650 2.6.3.4                       | pass           |
| Thermal Shock                      | IPC-TM-650 2.6.7.1                       | pass           |
| Temperature Humidity Aging         | IPC-TM-650 2.6.11.1                      | pass           |

\*Qualified independently by Pacific Testing Laboratories, Inc.



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



#### Как с нами связаться

**Телефон:** 8 (812) 309 58 32 (многоканальный)

**Факс:** 8 (812) 320-02-42

**Электронная почта:** [org@eplast1.ru](mailto:org@eplast1.ru)

**Адрес:** 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.