



# Scotch™

## Double Coated Laminating Adhesive 9495MP

---

### Product Data Sheet

---

Updated : July 2000

Supersedes : June 1995

---

#### Physical Properties

Not for specification purposes

<b>Adhesive</b>	2.0 thou (50 micron) #200MP Hi-Performance Acrylic
<b>Carrier</b>	0.5 thou (12.5 micron) Transparent Polyester
<b>Adhesive</b>	2.0 thou (50 micron) #200MP Hi-Performance Acrylic
<b>Liner</b>	4.0 thou (100 micron) 94g/m <sup>2</sup> 58# Polycoated Kraft 4.1
<b>Shelf Life</b>	24 months from date of manufacture when stored in cartons at 70°F at 50% relative humidity.

---

#### Features:

- A thin polyester carrier provides improved handling with ease of die cutting and laminating compared to free film adhesives.
- #200MP Hi - Performance acrylic adhesive provides exceptional temperature and chemical resistance and withstands tough application environments.
- Moisture - stable liner provides easy removal and improves processing of parts.

---

#### Applications

- Ideal for graphic overlays, nameplates, appliqués and decorative trim.
- Excellent for foam lamination.

---

#### Properties and Performance

Properties defined are based on the adhesion of impervious faceplate materials to a stainless steel test surface.  
(Not for specification purposes)

<b>Temperature Range</b>	#200MP adhesive has a temperature range of -40°C (-40°F) to 250°F (121°C) for days or weeks and to 300°F (149°C) for minutes or hours.
<b>Chemical Resistance</b>	Excellent solvent resistance when properly applied. The adhesive resists mild acids and alkalis, oil, gasoline, kerosene, JP-4 fuel and many other solvents. It is not recommended for total immersion.
<b>Humidity Resistance</b>	No adverse effect on the bond after exposure to 100% relative humidity at 100°F (38°C).

Date : July 2000  
Double Coated Laminating  
Adhesive 9495MP

### Properties and Performance Contd...

<b>U.V. Resistance</b>	Adhesive is resistant to oxidation and ozone when exposed to air or ultraviolet light.
<b>Bond Build Up</b>	The bond strength of #200MP adhesive increases as a function of time and temperature.

### Adhesion Properties Not for specification purposes

Initial Adhesion - Dynamic Peel 180° (ASTM D-3330, PSTC3)	
<b>Stainless Steel</b>	<b>4.0 N/10mm</b>

### Processing

#### Die Cutting:

Good die-cuttability. Lubricate dies with vanishing oil or similar low residue lubricants for improved processing.

#### Roll Laminating:

Use rubber over steel roll set up with moderate application pressure. Make adhesive to substrate contact a nip area only.

### Special Considerations

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact and thus improves bond strength.

To obtain adhesion, the bonding surfaces must be clean, dry, and smooth. Typical cleaning solvents are isopropyl alcohol or heptane. Consult solvent manufacturers Material Safety Data Sheet for proper handling and storage instructions.

Ideal tape application temperature range is 21°C to 38°C (70°F to 100°F) Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended because the adhesive becomes too firm to readily adhere. However, once properly applied, low temperature holding is satisfactory.

3M and Scotch are trademarks of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



### Tapes & Adhesives Group

3M United Kingdom PLC  
3M House, PO Box 1,  
Market Place,  
Bracknell, Berkshire,  
RG12 1JU

Product Information :  
  
Tel 0870 60 800 50  
Fax 0870 60 700 99

3M Ireland  
3M House, Adelphi Centre,  
Upper Georges Street,  
Dun Laoghaire, Co. Dublin,  
Ireland

© 3M United Kingdom PLC 2000

Customer Service :  
  
Tel (01) 280 3555  
Fax (01) 280 3509



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



#### Как с нами связаться

**Телефон:** 8 (812) 309 58 32 (многоканальный)

**Факс:** 8 (812) 320-02-42

**Электронная почта:** [org@eplast1.ru](mailto:org@eplast1.ru)

**Адрес:** 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.