

# 3M™ Very Low Outgassing Polyester Seal Tape 6692

## Product Description

The 3M™ Very Low Outgassing Polyester Seal Tape 6692 is a 3.0 mil total thickness low outgassing, polyester backed, single coated sealing tape for Hard Disk Drive assembly and related electronics sealing applications. This 2 mil metalized polyester backing offers a glossy visual appearance along with the functional properties of low static, low diffusivity, and high tensile strength. The low outgassing acrylic adhesive offers excellent chemical performance, high shear strength, and a permanent yet reworkable level of adhesion to a variety of substrate materials. The adhesive has been further enhanced to eliminate measurable organic acid from the outgassing signature. 3M™ Non-Silicone Polyester Liner 5932 completes the construction.

## Product Construction

Backing	Color	Adhesive	Liner
2 mil Metalized Polyester	Silver	Low Outgassing Acrylic	5932 Non-silicone

## Typical Physical Properties

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

ASTM Test Method		
<b>Adhesion to Stainless Steel:</b>		
(Initial, 15 min.)	18 oz./in.	D-3330, part F
(24 hrs. @ Room Temp.)	33 oz./in.	D-3330, part F
(24 hrs. @ 120°F)	52 oz./in.	D-3330, part F
(24 hrs. @ 150°F)	62 oz./in.	D-3330, part F
<b>Adhesion to Aluminum:</b>		
(Initial, 15 min.)	78 oz./in.	D-3330, part F
(24 hrs. @ Room Temp.)	79 oz./in.	D-3330, part F
(24 hrs. @ 120°F)	86 oz./in.	D-3330, part F
(24 hrs. @ 150°F)	89 oz./in.	D-3330, part F
<b>Tape Thickness:</b>	3.0 mils (0.076 mm)	D-3652
<b>Adhesive Thickness:</b>	1.0 mil (0.025 mm)	D-3652
<b>Release Liner Thickness:</b>	2.0 mils (0.051 mm)	D-3652
<b>Tensile Strength:</b>	52 lb./in. width (440 N/100 mm)	D-3759
<b>Elongation:</b>	120%	D-3759



# 3M™ Very Low Outgassing Polyester Seal Tape 6692

## Typical Chemical Properties

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

### Outgassing:

**Outgassing by Dynamic Headspace, 3 hr. @ 85°C, Quantify by GC-Mass Spec**

		ASTM Test Method
Hydrocarbons	< 100 ng/cm <sup>2</sup>	D-4526 <sup>1</sup>
Benzoic Acid	Not detected	D-4526 <sup>1</sup>
Total Organic Acids	Not detected	D-4526 <sup>1</sup>
Alkyl Acrylates / Esters	< 40 ng/cm <sup>2</sup>	D-4526 <sup>1</sup>
Phenols & Alcohols	< 50 ng/cm <sup>2</sup>	D-4526 <sup>1</sup>
Siloxanes	< 10 ng/cm <sup>2</sup>	D-4526 <sup>1</sup>
Total Outgassing	Not detected	D-4526 <sup>1</sup>

<sup>1</sup>Outgassing = Dynamic headspace analysis of volatile components collected during a 3 hr. @ 85°C heat cycle using a Hewlett-Packard Model 5890 Series II gas chromatograph coupled with a Hewlett-Packard 5989B Mass Spectrometer.

### Extractable Ionics:

**Water extractable ionics by IC, 1 hr. @ 85°C, Quantify by Ion Chromatography**

Fluoride	Not detected
Chloride	< 15 ng/cm <sup>2</sup>
Nitrate	Not detected
Bromide	Not detected
Phosphate	Not detected
Sulfate	Not detected

## General Information

- Storage and die cutting are preferred in controlled temperature and humidity environment. High humidity exposure can cause die cutting defects.
- Poor die cutting could lead to poor product quality.
- Weeds should be removed immediately.
- Rotary die cutting is recommended.
- Substrate should be smooth, clean, dry and oil-free to provide good wet-out and adequate adhesion.
- Adhesive should not be applied at temperatures < 50°F (10°C) [best if room temperature or higher].
- Custom sizes available.

## Application Ideas

- Sealing of Hard Disk Clamshells.
- Sealing of other electronic devices or instrumentation requiring a low outgassing adhesive tape product.
- Other permanent applications requiring an exceptionally high chemical purity, single coated tape.

# 3M™ Very Low Outgassing Polyester Seal Tape 6692

## Shelf Life

Product retains its performance for two years from date of manufacture when properly stored at 60-80°F (16-27°C) and 40-50% relative humidity condition.

## Certification/Recognition

**MSDS:** 3M has not prepared a MSDS for this product which is not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, the product should not present a health and safety hazard. However, use or processing of the product in a manner not in accordance with the directions for use may affect its performance and present potential health and safety hazards.

**TSCA:** This product is defined as an article under the Toxic Substances Control Act and therefore, it is exempt from inventory listing requirements.

**RoHS:** This product complies with the requirements of EU Directive 2002/95/EC and 2005/618/EC.

## For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-251-8634. Address correspondence to: 3M Electronics Markets Materials Division, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55144-1000. Our fax number is 651-778-4244 or 1-877-369-2923. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

## Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

## Warranty; Limited Remedy; Limited Liability.

This product will be free from defects in material and manufacture at the time of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.**



### Electronics Markets Materials Division

#### 3M Electronics

3M Center, Building 21-1W-10, 900 Bush Avenue  
St. Paul, MN 55144-1000  
1-800-251-8634 phone  
651-778-4244 fax  
[www.3M.com/electronics](http://www.3M.com/electronics)

3M is a trademark of 3M Company.  
Please recycle. Printed in U.S.A.  
© 3M 2008. All rights reserved.  
60-5002-0100-3





Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



#### Как с нами связаться

**Телефон:** 8 (812) 309 58 32 (многоканальный)

**Факс:** 8 (812) 320-02-42

**Электронная почта:** [org@eplast1.ru](mailto:org@eplast1.ru)

**Адрес:** 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.