

Water Insoluble Nitride Thin Film Precision Chip Resistors

WIN Series

- TaN thin film technology
- Inherent moisture protection superior to that of passivated nichrome chip resistors
- High stability in humid and polluted environments
- Typical 85°C, 85%RH biased humidity 2000 hour stability <0.1%
- Typical moisture resistance stability ± 100 ppm
- Precision $\pm 0.05\%$ tolerance and ± 10 ppm/°C
- Anti-sulfur terminations
- 100% screened by automated optical inspection



All Pb-free parts comply with EU Directive 2011/65/EU amended by (EU) 2015/863 (RoHS3)

Electrical Data

| | | T0402 | T0603 | T0805 | T1206 |
|--|------------|-------------------------|----------------------------------|------------|-----------|
| Power rating @ 70°C | watts | 0.05 | 0.1 | 0.25 | 0.33 |
| Resistance range | ohms | 7R5 to 30K | 5R to 100K | 5R to 267K | 5R to 1M0 |
| Limiting element voltage (maximum voltage) | Vdc or rms | 75 | 75 | 100 | 200 |
| Resistance tolerance | % | $\pm 0.1 \pm 0.5 \pm 1$ | $\pm 0.05 \pm 0.1 \pm 0.5 \pm 1$ | | |
| TCR | ppm/°C | $\pm 50 \pm 25$ | $\pm 10 \pm 15 \pm 25 \pm 50$ | | |
| Standard values | | E24, E96, E192 | | | |
| Ambient temperature range | °C | -65 to +150 | | | |

Physical Data

| Dimensions in mm & (inch) and weight in mg | | | | | | | |
|--|--|--|--|--|-----------------|--|---------|
| | L | W | T | C | B min | A | Wt. nom |
| T0402 | 1.02 \pm 0.05 (0.04 \pm 0.002) | 0.53 \pm 0.05 (0.021 \pm 0.002) | 0.3 \pm 0.08 (0.012 \pm 0.003) | 0.2 \pm 0.05 (0.008 \pm 0.002) | 0.44 (0.017) | 0.25 \pm 0.05 (0.01 \pm 0.002) | 0.9 |
| T0603 | 1.58 \pm 0.15 (0.062 \pm 0.006) | 0.80 \pm 0.10 (0.031 \pm 0.004) | 0.45 \pm 0.10 (0.018 \pm 0.004) | 0.27 \pm 0.20 (0.011 \pm 0.008) | 0.82 (0.032) | 0.34 \pm 0.20 (0.013 \pm 0.008) | 2.0 |
| T0805 | 2.02 \pm 0.15 (0.080 \pm 0.006) | 1.28 \pm 0.15 (0.050 \pm 0.006) | 0.45 \pm 0.10 (0.018 \pm 0.004) | 0.31 \pm 0.20 (0.012 \pm 0.008) | 1.1 (0.043) | 0.40 \pm 0.20 (0.016 \pm 0.008) | 4.3 |
| T1206 | 3.15 \pm 0.15 (0.124 \pm 0.006) | 1.57 \pm 0.15 (0.062 \pm 0.006) | 0.50 \pm 0.15 (0.020 \pm 0.006) | 0.45 \pm 0.25 (0.018 \pm 0.010) | 2.03 (0.08) | 0.52 \pm 0.25 (0.020 \pm 0.010) | 9.6 |



Construction

Conductors, thin film resistive element and epoxy outer protection are applied to an alumina substrate. The chips are supplied with wrap-around terminations suitable for soldering. The terminations have an electroplated nickel barrier and either 100% matt tin or 60/40 SnPb finish.

Marking & Solvent Resistance

WIN resistors have no marking on the component body. The body protection is resistant to all normal cleaning solvents suitable for printed circuits

Screening

WIN resistors can be screened to any tests identified in MIL-PRF-55342 and AEC-Q200 to provide components suitable as a COTS equivalent to MIL products or screened product subject to harsh operating environments.

General Note

TT Electronics reserves the right to make changes in product specification without notice or liability. All information is subject to TT Electronics' own data and is considered accurate at time of going to print.

Manufacturing Capabilities Data

| TCR ppm/°C | Tolerance % | | | | | | |
|---------------|-------------|-----------|-----------|------------|-----------|------------|---------|
| | T0402 | T0603 | | T0805 | | T1206 | |
| | 0.1-1 | 0.05 | 0.1-1 | 0.05 | 0.1-1 | 0.05 | 0.1-1 |
| 10 | | 5kΩ-10kΩ | | 5kΩ-40kΩ | | 5kΩ-80kΩ | |
| 15 | | 100Ω-50kΩ | | 100Ω-100kΩ | | 100Ω-400kΩ | |
| 25 | 10Ω-30kΩ | 50Ω-50kΩ | 10Ω-100kΩ | 50Ω-100kΩ | 10Ω-267kΩ | 50Ω-400kΩ | 10Ω-1MΩ |
| 50 | 7.5Ω-30kΩ | | 5Ω-100kΩ | | 5Ω-267kΩ | | 5Ω-1MΩ |

Performance Data

| Test | Method | ΔR | |
|------------------------------|---|-------------------------------|---------------------------------|
| | | MIL-PRF-55342 Limits (max) | WIN actual performance (typ) |
| Thermal Shock | MIL-PRF-55342 4.8.3 (MIL-STD-202 107G cond. F: 5 cycles in air, +150 / -65°C) | ± 0.1% | ± 0.01% |
| Thermal Shock - Extended | MIL-STD-202 107G cond. F-3: 100 cycles in air, +150 / -65°C | ± 0.1% | ± 0.02% |
| Low Temp. Operation | MIL-PRF-55342 4.8.5 (-65°C) | ± 0.1% | ± 0.02% |
| Short Time Overload | MIL-PRF-55342 4.8.6 (lesser of 6.25 x Pr or 2 x LEV for 5 seconds) | ± 0.1% | ± 0.02% |
| High Temp. Exposure | MIL-PRF-55342 4.8.7 (+150°C for 100 hours) | ± 0.1% | ± 0.02% |
| High Temp. Exposure Extended | +150°C for 1000 hours | N/A | ±0.1% |
| Resistance to Solder Heat | MIL-PRF-55342 4.8.8 | ± 0.2% | ± 0.02% |
| Moisture Resistance | MIL-PRF-55342 4.8.9 (MIL-STD-202 106G: 10 cycles, 65±2°C, 95±5% RH) | ± 0.2% | ± 0.01% |
| Load Life | MIL-PRF-55342 4.8.11 (MIL-STD-202 108A: Pr at 70°C for 2000 hours) | ± 0.5% | ± 0.08% |
| Biased Damp Heat | 85°C, 85%RH, 10% Pr bias, for 2000 hours | N/A | ± 0.08% |
| Flower of Sulfur | ASTM B-809 (modified) 105°C Dry, 1000 Hours | | Pass |



General Note

TT Electronics reserves the right to make changes in product specification without notice or liability. All information is subject to TT Electronics' own data and is considered accurate at time of going to print.



Ordering Procedure

This product has two valid part numbers:

European (Welwyn) Part Number: WINT1206LF031001B3 (1206, $\pm 25\text{ppm}/^\circ\text{C}$, 1 kilohm $\pm 0.1\%$, Pb-free)



| 1 | 2 | 3 | 4 | 5 | 6 | 7 |
|--------|-------|--------------|--|---|------------------|----------------------|
| Series | Type | Termination | TCR | Value | Tolerance | Packing |
| WIN | T0402 | PB = SnPb | 12 = $\pm 10\text{ppm}/^\circ\text{C}$ | 3 digits + multiplier R = ohms for values <100 ohms | A = $\pm 0.05\%$ | Tape & reel |
| | T0603 | LF = Pb free | 11 = $\pm 15\text{ppm}/^\circ\text{C}$ | | B = $\pm 0.1\%$ | 3 3000/reel Standard |
| | T0805 | | 03 = $\pm 25\text{ppm}/^\circ\text{C}$ | | D = $\pm 0.5\%$ | Blank 1000/reel |
| | T1206 | | 02 = $\pm 50\text{ppm}/^\circ\text{C}$ | | F = 1% | |

USA (IRC) Part Number: WIN -T1206LF-03-1001-B3 (1206, $\pm 25\text{ppm}/^\circ\text{C}$, 1 kilohm $\pm 0.1\%$, Pb-free)



| 1 | 2 | 3 | 4 | 5 | 6 | 7 |
|--------|-------|--------------|--|---|------------------|----------------------|
| Series | Type | Termination | TCR | Value | Tolerance | Packing |
| WIN | T0402 | PB = SnPb | 12 = $\pm 10\text{ppm}/^\circ\text{C}$ | 3 digits + multiplier R = ohms for values <100 ohms | A = $\pm 0.05\%$ | Tape & reel |
| | T0603 | LF = Pb free | 11 = $\pm 15\text{ppm}/^\circ\text{C}$ | | B = $\pm 0.1\%$ | 3 3000/reel Standard |
| | T0805 | | 03 = $\pm 25\text{ppm}/^\circ\text{C}$ | | D = $\pm 0.5\%$ | Blank 1000/reel |
| | T1206 | | 02 = $\pm 50\text{ppm}/^\circ\text{C}$ | | F = 1% | |

General Note

TT Electronics reserves the right to make changes in product specification without notice or liability. All information is subject to TT Electronics' own data and is considered accurate at time of going to print.



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный)

Факс: 8 (812) 320-02-42

Электронная почта: org@eplast1.ru

Адрес: 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.