

# 3M™ Heat Shrink Tubing MFP

## Modified Polyvinylidene Fluoride

Data Sheet

September 2013

---

**Description** 3M™ Heat Shrink Tubing MFP is a cross-linked, thin-walled, heat-shrinkable tubing offering a high degree of mechanical strength and high-temperature resistance. Fabricated from polyvinylidene fluoride, the tubing has outstanding abrasion resistance and cut-through properties in combination with high dielectric strength. It is inherently flame retardant, semi-rigid and highly resistant to most industrial fuels, chemicals and solvents. When heated in excess of 347°F (175°C), MFP tubing rapidly shrinks to a skintight fit.

---

**Agency Approvals & Self Certifications**

Meets requirements of:

- SAE-AMS-DTL-23053/8 and functional requirements of 23053/18, Class 1\*
- AMS-3632
- UL Listed, UL File E-39100, VW-1
- CSA LR38227, OFT

\*Formerly: MIL-I-23053/8 and MIL-DTL-23053/8  
MIL-I-23053/18 and MIL-DTL-23053/18

---

**Applications**

MFP tubing is typically used for shrink-fit protection and strain relief of wires, solder joints, terminals and connections. Suggested applications include automotive wiring, jackets, fuse coverings and military wire markers. Because the tubing is transparent, it allows see-through inspection and identification, and is ideal for use as a jacketing for components such as resistors and capacitors. The tubing is readily marked by hot-stamp and print-wheel equipment.

---

**Shrink Ratio**

MFP tubing has a 2:1 shrink ratio. When freely recovered, the tubing will shrink to 50% of its as-supplied internal diameter. The recovered wall thickness is proportional to the degree of recovery.

The operating temperature range is from -55°C (-67°F) to 175°C (347°F), with a shrinking temperature minimum of 175°C (347°F)

---

# 3M™ Heat Shrink Tubing MFP

## Standard Sizes and Dimensions

| Ordering Size (Nominal) | Expanded I.D. (Minimum) |         | Recovered I.D. (Maximum) |         | Total Recovered Wall Thickness (Nominal) |        |
|-------------------------|-------------------------|---------|--------------------------|---------|--|--------|
|                         | In.                     | (mm)    | In.                      | (mm)    | In.                                      | (mm)   |
| 3/64                    | .046                    | (1,17)  | .023                     | (0,58)  | .010                                     | (0,25) |
| 1/16                    | .063                    | (1,60)  | .031                     | (0,79)  | .010                                     | (0,25) |
| 3/32                    | .093                    | (2,36)  | .046                     | (1,17)  | .010                                     | (0,25) |
| 1/8                     | .125                    | (3,18)  | .062                     | (1,57)  | .010                                     | (0,25) |
| 3/16                    | .187                    | (4,75)  | .093                     | (2,36)  | .010                                     | (0,25) |
| 1/4                     | .250                    | (6,35)  | .125                     | (3,18)  | .012                                     | (0,30) |
| 3/8                     | .375                    | (9,53)  | .187                     | (4,75)  | .012                                     | (0,30) |
| 1/2                     | .500                    | (12,70) | .250                     | (6,35)  | .012                                     | (0,30) |
| 5/8                     | .625                    | (15,88) | .313                     | (7,94)  | .014                                     | (0,36) |
| 3/4                     | .750                    | (19,05) | .375                     | (9,53)  | .017                                     | (0,43) |
| 1                       | 1.000                   | (25,40) | .500                     | (12,70) | .019                                     | (0,48) |

## Typical Properties

Not for specifications. Values are typical, not to be considered minimum or maximum. Properties measured at room temperature 73°F (23°C) unless otherwise stated.

| Physical Property   | Typical Value |
|---|---------------|
| Tensile Strength  | 5500 PSI      |
| Ultimate Elongation   | 350%          |
| Longitudinal Change   | +1, -10%      |
| Secant Modulus (2%)   | 123,000 PSI   |
| Specific Gravity  | 1.7           |
| Low Temperature Flexibility (outer wall only)<br>4 hrs @ -55 °C | No cracking   |
| Flammability<br>Self-extinguishing, UL24 VW-1 Test              | Pass          |

| Electrical Property (Test Method) | Typical Value<br>US units (metric) |
|-----------------------------------|------------------------------------|
| Dielectric Strength               | 900 V/mil                          |
| Volume Resistivity                | 10 <sup>14</sup> ohm/cm            |

| Chemical Property (Test Method) | Typical Value |
|---------------------------------|---------------|
| Corrosion Resistance            | Non-corrosive |
| Fuel & Oil Resistance           | Excellent     |
| Solvent Absorption              | Excellent     |
| Abrasion Resistance             | Excellent     |
| Acid & alkalis Resistance       | Excellent     |

# 3M™ Heat Shrink Tubing MFP

---

**Standard Colors**

Clear

Also available in Black. Price, MOQ and Lead Time will vary for these colors. Please contact Local Sales Representative or Customer Service Representative for more information.

---

**Shelf Life & Storage**

3M™ Heat Shrink Tubing MFP has a 10-year shelf life from date of manufacture when stored in a humidity controlled storage (10°C/50°F to 27°C/80°F and <75% relative humidity).

---

**Availability****Standard Packaging**

Four-foot lengths. Colors available are subject to factory quotation.

Please contact your local distributor; available from [3M.com/oem](http://3M.com/oem) [Where to Buy] or call 1-800-676-8381.

---

**Important Notice**

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product, which are not contained in 3M's current publications, or any contrary statements contained on your purchase order, shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

---

**Warranty; Limited Remedy; Limited Liability**

This product will be free from defects in material and manufacture at the time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.

---

3M is a trademark of 3M Company.



Electrical Markets Division  
6801 River Place Blvd.  
Austin, TX 78726-9000  
800 676.8381  
FAX: 800 828.9329  
[www.3M.com/oem](http://www.3M.com/oem)

Please recycle  
© 3M 2013 All rights reserved  
78-8127-6766-9 Rev F



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



#### Как с нами связаться

**Телефон:** 8 (812) 309 58 32 (многоканальный)

**Факс:** 8 (812) 320-02-42

**Электронная почта:** [org@eplast1.ru](mailto:org@eplast1.ru)

**Адрес:** 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.