

SPECIFICATION CONTROL DRAWING


82A1111

TITLE RADIATION-CROSSLINKED, MODIFIED, FLUOROPOLYMER-INSULATED, ONE CONDUCTOR CABLE, SHIELDED, JACKETED, LIGHTWEIGHT, FLEXIBLE

Date 12-2-91

Revision C

This specification sheet forms a part of the latest issue of Raychem Specification 80.



CABLE CONSTRUCTION DETAILS

PART NUMBER	CONDUCTOR SIZE (AWG)	SHIELD SIZE (AWG)	JACKET THICKNESS (inches)		OUTSIDE DIAMETER (inches)		MAXIMUM WEIGHT (lb/1000 ft)
			MINIMUM	NOMINAL	NOMINAL	MAXIMUM	
82A1111-28-*	28	38	.005	.007	.060	.065	4.0
82A1111-26-*	26	38	.005	.007	.064	.069	4.7
82A1111-24-*	24	38	.005	.007	.068	.073	5.7
82A1111-22-*	22	38	.005	.007	.074	.079	6.9
82A1111-20-*	20	38	.005	.007	.084	.089	8.9
82A1111-18-*	18	38	.006	.008	.097	.102	12.5
82A1111-16-*	16	38	.006	.008	.112	.118	17.1
82A1111-14-*	14	38	.007	.009	.134	.141	25.3
82A1111-12-*	12	38	.008	.010	.158	.166	35.8
82A1111-10-*	10	38	.008	.011	.196	.206	56.7
82A1111- 8-*	8	38	.009	.012	.236	.248	84.7
82A1111- 6-*	6	38	.011	.014	.281	.295	126.
82A1111- 4-*	4	36	.013	.017	.373	.392	208.
82A1111- 2-*	2	36	.014	.019	.444	.466	302.
82A1111- 1-*	1	34	.016	.021	.513	.539	385.
82A1111- 0-*	0	34	.018	.024	.590	.620	491.
82A1111-00-*	00	34	.020	.026	.644	.676	597.

CABLE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C

Maximum continuous conductor temperature

VOLTAGE RATING: 600 volts (rms)

* BLOCKING: 150 ± 3°C

CROSSLINKING PROOF TEST: 300 ± 3°C for 7 hours

15 in. specimen with sufficient weight to keep straight

DIELECTRIC WITHSTAND: 1500 volts (rms), 60 Hz

* FLAMMABILITY: Procedure 1, 3 seconds (maximum); 3 in. (maximum)

JACKET COLOR: White preferred

JACKET ELONGATION AND TENSILE STRENGTH:

Elongation, 100% (minimum)

Tensile Strength, 3000 lbf/in² (minimum)

JACKET FLAWS:

Spark Test, 1500 volts (rms), 60 Hz, 100% test

Impulse Dielectric Test, 6.0 kV (peak), 100% test

* LIFE CYCLE: 200 ± 3°C for 168 hours

* LOW TEMPERATURE-COLD BEND: -65 ± 3°C

* SECANT MODULUS: 4.0 X 10⁴ lbf/in² (maximum), 2 % strain, 2 in. Jaw separation, 0.2 in. / minute, procedural reference ASTM D 882

SHIELD COVERAGE: 85% (minimum)

VOLTAGE WITHSTAND (POST ENVIRONMENTAL):

1000 volts (rms), 60 Hz, 1 minute

PART NUMBER

The *** in the part number above shall be replaced by a color code designator with a dash separating the component wire color from the jacket color.

Example: AWG 20, white component wire; white jacket: 82A1111-20-9-9

* Qualification Test

COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-881.

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL.

Raychem

Raychem Corporation
300 Constitution Drive, Menlo Park, California 94025
(415) 361 3333 TWX 910 373 1728



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный)

Факс: 8 (812) 320-02-42

Электронная почта: org@eplast1.ru

Адрес: 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.