



HIGH CONDUCTIVITY THERMAL GAP FILLING PADS

Aavid utilizes a proprietary fiber orientation technology to produce highly thermally conductive materials that are utilized in these unique gap filling pads. Our Aavid SuperThermal line of TIMs deliver the high conductivity of carbon fiber without sacrificing the flexibility and adhesion capabilities of a polymer. The SuperThermal pads and sheets are ideal for cooling high heat sources such as CPUs, GPUs and high density LEDs. This line includes pads made from specialized organic materials with extremely high thermal conductivity and low volume resistance.

SIZES

SuperThermal Interface Pads are available in full sheets that Aavid can cut and shape to suit your needs. They are also available in easy to use 25.4mm x 25.4mm (1" x 1") and 76.2mm x 76.2mm (3" x 3") pads for quick and simple assembly. For full sheet sizes please contact Aavid.

PART NUMBERS

Aavid Gap Pads part numbers are made up of six parts that represent the product, thickness, adhesion and shape. Instructions on how to build your part numbers are available in the document [Building an Aavid Gap Pad Part Number](#).



FEATURES:

- Extremely High Thermal Conductivity
- Low Thermal Resistance
- Flexible, Easy Contouring
- Adhesive & Non-Adhesive Options
- Puncture, Shear and Tear Resistant

SUPERTHERMAL PRODUCT LINE DETAILS¹

| Product Name | SuperThermal A072 | SuperThermal B132 | SuperThermal C128 | SuperThermal D089 |
|--|----------------------|----------------------|----------------------|----------------------|
| Thermal Properties | | | | |
| Thermal Conductivity (W/mK) | 7.2 | 13.2 | 12.8 | 8.9 |
| Operating Temp. Range (°C) | -40° - 150° | -40° - 150° | -40° - 150° | -40° - 150° |
| Thermal Resistance at 10psi (at % Strain) ² | 2.0 (at 18%) | 1.1 (at 19%) | 0.78 (at 9.6%) | 0.98 (at 22%) |
| Thermal Resistance at 20psi (at % Strain) ² | 1.9 (at 27%) | 1.1 (at 26%) | 0.72 (at 16%) | 0.84 (at 24%) |
| Thermal Resistance at 40psi (at % Strain) ² | 1.6 (at 31%) | 0.98 (at 39%) | 0.60 (at 30%) | 0.58 (at 29%) |
| Mechanical Properties | | | | |
| Color | Black/ Dark Grey | Grey | Black | Black |
| Adhesion | Double-Sided | Double-Sided | Non-Adhesive | Non-Adhesive |
| Base Material | Silicone | Silicone | Silicone | Silicone |
| Carrier / Reinforcement | PET Film | PET Film | PET Film | PET Film |
| Hardness (ASTM D2240, Shore 00) | 63 | 55 | 65 | 77 |
| Density (g/cm ³) | 1.8 | 2.4 | 2.4 | 2.4 |
| Tensile Strength (kPa) | 33 | 22 | 16 | 44 |
| Thickness Availability (mm) | 1, 2 or 3mm | 1, 2 or 3mm | 0.5 or 1mm | 0.2 or 1mm |
| Electrical Properties | | | | |
| Volume Resistivity (Ω-m) | ≥10 ¹⁰ | ≥10 ¹⁰ | <100 | <100 |
| Breakdown Voltage (kVAC) | >1.0 | >0.9 | <0.1 | <0.1 |
| Flammability Rating UL94 | V-0 | V-0 | V-0 | V-0 |

¹ Measurement is for 1mm thickness, information on additional thicknesses is available on request.

² Strain is the ratio of the reduction in pad thickness to the initial thickness of the pad. Thermal resistance is measured in (°C x cm²/W).



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный)

Факс: 8 (812) 320-02-42

Электронная почта: org@eplast1.ru

Адрес: 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.