

Eccosorb® MCS

High-Loss, Thin, Elastomeric Microwave Absorber



HIGH-LOSS ELASTOMERIC ABSORBER

Eccosorb MCS is a thin, flexible, high-loss, magnetically loaded, electrically non-conductive silicone rubber sheet. It is designed for the frequency range from 800 MHz to 18 GHz. The material is impervious to moisture and can be subjected to high altitudes with no adverse effects. Being a silicone based absorber, it has low out-gassing properties for space applications.

FEATURES AND BENEFITS

- High power performance
- Low outgassing properties
- High magnetic loss

Commercial Telecom

MARKETS

- Security and Defense
- Automotive and Industrial Electronics

SPECIFICATIONS

TYPICAL PROPERTIES	ECCOSORB MCS
Frequency Range (GHz)	0.8 to 18
Max Service Temperature °C (°F)	170 (338)
Fire Retardancy	UL94 V-0
Hardness (Shore A)	>80
Volume Resistivity (ohm-cm)	2x 10 ⁸
Weight kg/m² (lbs/ft²)	4.4 (0.9)
Relative Impedance	0.66 – 0.23
Tensile Strength (MPa)	>3.5
Elongation (%)	>20
Dielectric Strength (volts/mil)	>20
Outgassing	
(%TML) (%CVCM)*	0.3/0.05

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

APPLICATIONS

- When placed within a cavity, Eccosorb MCS has proven to be very effective at dampening resonances due to the absorbers high permittivity and permeability as well as high loss values, which in turn reduces the overall VSWR.
- It is designed for the suppression of surface currents over a wide range of frequencies.
- It can be used for the suppression of creeping waves and reduction of cavity resonances in microwave modules.
- It is also useful in reducing RF coupling of antennas and microwave components.

AVAILABILITY

- Standard sheets are 305 x 305mm (12"x12"), standard thickness is 1 mm (.040")
- It can be supplied with a Pressure Sensitive Adhesive (PSA)
- Eccosorb MCS is available in other sizes, thicknesses and customer specified configurations upon request.

Americas: +1.866.928.8181 Europe: +49.(0)8031.2460.0 Asia: +86.755.2714.1166

^{*} Outgassing data per ASTM E595-07; criteria for acceptability is 1.00% TML and 0.10% CVCM.




Eccosorb® MCS

INSTRUCTIONS FOR USE

- Eccosorb MCS is designed to function directly in front of a metallic surface.
- The material can be bonded by use of an RTV silicone based adhesive in conjunction with a suitable primer.
- To obtain a strong bond of the absorber to the object, the metallic surface should first be thoroughly cleaned with a degreasing solvent.
- Eccosorb MCS can be readily cut with a sharp knife and template.
 It is a very flexible material and conforms to contoured surfaces.

Typical Attenuation Eccosorb MCS





Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001:
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



Как с нами связаться

Телефон: 8 (812) 309 58 32 (многоканальный)

Факс: 8 (812) 320-02-42

Электронная почта: org@eplast1.ru

Адрес: 198099, г. Санкт-Петербург, ул. Калинина,

дом 2, корпус 4, литера А.