

# SPECIFICATION CONTROL DRAWING

**55A4831**

**TITLE** THREE CONDUCTOR CABLE, RADIATION-CROSSLINKED, MODIFIED ETFE, JACKETED, NORMAL WEIGHT, 600 VOLT

**Date** 4-27-93

**Revision** B

This specification sheet forms a part of the latest issue of Raychem Specification 55A.

COMPONENT WIRES - 55A0811

JACKET - RADIATION-CROSSLINKED, MODIFIED ETFE



### CONSTRUCTION DETAILS

PART NUMBER	CONDUCTOR SIZE (AWG)	JACKET THICKNESS (inches)		OUTSIDE DIAMETER (inches)		MAXIMUM WEIGHT (lbs/1000 ft.)
		MINIMUM	NOMINAL	NOMINAL	MAXIMUM	
55A4831-26-*	26	.006	.008	.101	.107	7.0
55A4831-24-*	24	.006	.008	.112	.118	9.1
55A4831-22-*	22	.006	.008	.125	.131	12.5
55A4831-20-*	20	.006	.008	.142	.148	17.8
55A4831-18-*	18	.006	.008	.166	.173	25.8
55A4831-16-*	16	.006	.008	.183	.190	31.9
55A4831-14-*	14	.007	.009	.222	.230	47.8
55A4831-12-*	12	.007	.009	.259	.269	69.9
55A4831-10-*	10	.007	.009	.311	.326	143.

### CABLE RATINGS AND ADDITIONAL REQUIREMENTS

**TEMPERATURE RATING:** 150°C

Maximum continuous conductor temperature

**VOLTAGE RATING:** 600 volts (rms)

**ACCELERATED AGING:** 300 ± 3°C for 7 hours

\* **BLOCKING:** 200 ± 3°C for 6 hours

**DIELECTRIC WITHSTAND:** 1500 volts (rms), 60 Hz

**FLAMMABILITY:** Procedure 1, 3 seconds (maximum);

3 inch (maximum); no flaming of facial tissue

**JACKET COLOR:** White preferred

**JACKET ELONGATION AND TENSILE STRENGTH:**

Elongation, 50% (minimum)

Tensile Strength, 5000 lb/in<sup>2</sup> (minimum)

\* **LIFE CYCLE:** 200 ± 3°C for 168 hours

**LOW TEMPERATURE-COLD BEND:** -65 ± 3°C for 4 hours

**VOLTAGE WITHSTAND TEST (POST ENVIRONMENTAL):**

1000 volts, 60 Hz, 1 minute

**PART NUMBER**

The \*\*\* in the part numbers above shall be replaced by color code designators with a slash separating the component wire colors and a dash separating the component wire colors from the jacket color.

Example: AWG 20, white, black and red component wires; white jacket: 55A4831-20-9/0/2-9

**NOTE:** Nominal values are for information only.  
Nominal values are not requirements

\* Qualification Test

COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681.

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL.

## Raychem

Raychem Corporation  
300 Constitution Drive, Menlo Park, California 94025  
(415) 361 3333 TWX 910 373 1728



Компания «ЭлектроПласт» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов;
- Поставка более 17-ти миллионов наименований электронных компонентов;
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- Лицензия ФСБ на осуществление работ с использованием сведений, составляющих государственную тайну;
- Поставка специализированных компонентов (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Aeroflex, Peregrine, Syfer, Eurofarad, Texas Instrument, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Помимо этого, одним из направлений компании «ЭлектроПласт» является направление «Источники питания». Мы предлагаем Вам помощь Конструкторского отдела:

- Подбор оптимального решения, техническое обоснование при выборе компонента;
- Подбор аналогов;
- Консультации по применению компонента;
- Поставка образцов и прототипов;
- Техническая поддержка проекта;
- Защита от снятия компонента с производства.



#### Как с нами связаться

**Телефон:** 8 (812) 309 58 32 (многоканальный)

**Факс:** 8 (812) 320-02-42

**Электронная почта:** [org@eplast1.ru](mailto:org@eplast1.ru)

**Адрес:** 198099, г. Санкт-Петербург, ул. Калинина, дом 2, корпус 4, литера А.